

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0506

Product Size:

NPS 24 SCH 120

Production Date:

October 18, 2012

Production Method:

Hot Expansion

Product Standards:

Product Heat Treatment: As-rolled

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 24 SCH 120 HEAT BSM-0506 (PIPE # LENGTH MASS) 429.41b/ft NDE SMLS NACE MR0175 2012/10 MADE IN CANADA.

ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

BSM-0506	Heat		
Heat	Test Type		
24	NPS		
SCH 120	Thickness	Wall	Product Detail
6	Pieces		S
DRL	Length		
429.40	lb/ft	Mass	
\$	μR/hr	Geiger	0.000
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	10 10 10 10 10
Pass	OD		Non-Dest
Pass	WT	TU	Destructive T
Pass	ASTM E213	TU	Testing
Pass	ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

	BS	Heat		Γ
	BSM-0506			
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.19	0.20	С		
0.92	0.89	Μ		
0.013	0.016 0.003	P		
0.004	0.003	S		Chemical
0.92 0.013 0.004 0.30 0.03 0.04	0.33	Si		Chemical Analysis (wt%)
0.03	0.04	Ç		(wt%)
0.04	0.06	Cu		
0.01	0.01	Mo		1000 m
0.03	0.02	Z.		
0.003	0.003	<	-	
0.002	0.002	=		
0.001	0.001	Nb		
0.0001	0.0002	В		
0.36	30	(IIW)	Œ	
0.36		(CSA)	Э	

BSM-0506 Heat	Heat Test Type		
Ferrite & Pearlite	Microstructure		
76	HRBW	Hardness	
Pass	Flattening Test		Mechar
Longitudinal; 19.1mm x WT	50mm GL	Tension Test	Mechanical Properties
46,400	psi	Yield (Rt0.5)	
45,300	psi	Yield (Rp0.2)	
73,000	psi	Tensile (Rm)	
0.64	(Rt0.5/Rm)	Τ/Υ	
48	%	Elongation (A)	

Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the / We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product.
- This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

* Note that this product was hydrotested to 1000psi for 5 seconds.

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.