

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0507

October 18, 2012

Production Method: Hot Expansion

Product Size:

NPS 24 SCH 120

Production Date:

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 24 SCH 120 HEAT BSM-0507 (PIPE # LENGTH MASS) 429.4lb/ft NDE SMLS NACE MR0175 2012/10 MADE IN CANADA.

BSM-0507	Heat		
Heat	Test Type		
24	NPS		
SCH 120	Thickness	Wall	Product Details
ω	Pieces		ls
DRL	Length		
429.40	lb/ft	Mass	
%	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-L
Pass	WT	S	estructive .
Pass	ASTM E213	TU	e Testing
Pass	ASTM E309	ET	
*	×	HydroTest	
Plain End	Condition	End	

		BSN	T_		Γ
		BSM-0507	Heat		
	Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
	Product	Heat	Analysis		
	0.19	0.20	C		
	0.90	0.87	Mn		
	0.013	0.014	P		
	0.002	0.002	S	***	Chemica
10	0.29	0.32	Si		Chemical Analysis (wt%)
	0.04	0.05	Cr		(wt%)
	0.05	0.05	Cu		
	0.01	0.01	Mo		
	0.04	0.03	N.		
	0.004	0.003	٧		
	0.003	0.002	Ti		8
	100.0	0.001	Nb		
70	0.0001	0.0001	В		
	0.36		(IIW)	CE	
	0.36	1	(CSA)	CE	

				Mechan	Mechanical Properties					
			Hardness		Tension Test	Yield (Rt0.5)	Yield (Rp0.2)	Tensile (Rm)	Τ/Υ	Elongation (A)
Heat	Test Type	Microstructure	HRBW	Flattening Test	50mm GL	psi	psi	psi	(Rt0.5/Rm)	%
BSM-0507	Heat	Ferrite & Pearlite	74	Pass	Transverse; 38.1mm x WT	48,200	48,900	72,000	0.67	42
					Longitudinal; 38.1mm x WT	39,600	37,800	71,000	0.56	49

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

* Note that this pipe was hydrotested at 1000psi for 5 seconds

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.