

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Seamless Carbon Steel Pipe Product Heat Number:

> BSM-0509 Product Size:

NPS 24 SCH 120

Production Date: October 18, 2012

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 24 SCH 120 HEAT BSM-0509 (PIPE # LENGTH MASS) 429.4lb/ft NDE SMLS NACE MR0175 2012/10 MADE IN CANADA.

BSM-0509	Heat		
Heat	Test Type		
24	NPS		
SCH 120	Thickness	Wall	Product Detail
ω	Pieces		S
DRL	Length	8	
429.40	lb/ft	Mass	
\$	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-E
Pass	WT	T	Destructive 1
Pass	ASTM E213	TU	esting
Pass	ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

	BSM-0509	Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.19	0.20	C	A STATE OF THE STA	
0.90	0.88	Mn		
0.012	0.015	70		
0.004	0.003	S		Chemical Analysis (wt%)
0.28	0.31	Si		Analysis
0.03	0.06	Cr		(wt%)
0.06	0.05	Cu		
0.01	0.00	Mo		
0.03	0.03	Z.		
0.004	0.003	<		
0.002	0.002	=1		
0.001	0.001	Nb		
0.0001	0.0001	В		
0.35	t	(WII)	CE	
0.36	1	(CSA)	Œ	

	BSM-0509	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	76	HRBW	Hardness	
	Pass	Flattening Test		Mecha
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
43,900	48,700	psi	Yield (Rt0.5)	
42,300	47,200	psi	Yield (Rp0.2)	
73,000	73,500	psi	Tensile (Rm)	
0.60	0.66	(Rt0.5/Rm)	Τ/Υ	
50	41	%	Elongation (A)	

Additional Details:

and that the results meet the corresponding requirements. Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, \checkmark We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

* Note that this product was hydrotested to 1000psi for 5 seconds.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. Manager of Quality and R&D

20120ct25