

## Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0578

Product Size:

NPS 16 SCH 160

Production Date:

November 29, 2012

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 16 SCH 160 HEAT BSM-0578 (PIPE # LENGTH MASS) 245.11b/ft NDE SMLS NACE MR0175 2012/11 MADE IN CANADA.

BSM-0578	Heat		
Heat	Test Type		
16	NPS		
SCH 160	Thickness	Wall	Product Details
00	Pieces		S
DRL	Length	1.00	
245.10	lb/ft	Mass	
<b>%</b>	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-L
Pass	TW	TU	estructive '
Pass	ASTM E213	TU	Testing
Pass	ASTM E309	ET	
-		HydroTest	
Plain End	Condition	End	

BSM-0578		Heat		
Vacuum Degas; Fully Killed	78 Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.21	0.21	C		
0.88	0.89	Μ'n		
0.004	0.006	P		
0.011	0.011	S		Chemical
0.21	0.23	Si		Chemical Analysis (wt%)
0.08	0.07	Ç		(wt%)
0.04	0.06	Cu		
0.04	0.05	Mo		
0.03	0.03	Z.		
0.002	1	<		
0.001	0.001	П		
0.001	0.001	Nb		
0.0004	0.0008	В		
0.39	•	(IIW)	æ	
0.39	1	(CSA)	Œ	

	BSM-0578 Heat	Heat	ALC .	
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	77	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 19.1mm x WT	Transverse; 19.1mm x WT	50mm GL	Tension Test	Mechanical Properties
35,600	45,500	psi	Yield (Rt0.5)	
34,500	48,500	psi	Yield (Rp0.2)	
71,500	78,000	psi	Tensile (Rm)	
0.50	0.58	(Rt0.5/Rm)	Τ/Υ	
49	37	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

√ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. 2012 Declo

Manager of Quality and R&D