

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 **Bri-Steel Manufacturing Inc.** www.brichemsteel.com Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0584

Product Size:

NPS 20 TRUE80

Production Date: December 4, 2012

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 20 TRUE80 HEAT BSM-0584 (PIPE # LENGTH MASS) 208.91b/ft NDE SMLS NACE MR0175 2012/12 MADE IN CANADA.

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

BSM-0584	Heat		
Heat	Test Type		
20	NPS		9
TRUE80	Thickness	Wall	Product Detail
7	Pieces		s
DRL	Length		
208.90	lb/ft	Mass	
Ġ	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-E
Pass	WT	IN	estructive T
Pass	ASTM E213	TU	ve Testing
Pass	ASTM E309	ET	
*	3	HydroTest	
Plain End	Condition	End	

50.7	BSN.	I		
0.00	RSM-0584	Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.21	0.20	C		
0.91	0.90	Mn		
0.014	0.012	P		
0.21 0.91 0.014 0.006	0.006	S		Chemical
0.28	0.32	Si		Chemical Analysis (wt%)
0.04	0.04	ç.		(wt%)
0.05	0.06	Cu		
0.01	0.01	Mo		
0.02	0.02	Ni		
0.003	0.003	٧		
0.003	0.003	Ħ		
0.001	0.001	Nb		
0.0002	0.0002	В		
0.38	-	(IIW)	Œ	
0.39	·	(CSA)	æ	

				Mechan	Medianical Froberties					
900		8	Hardness		Tension Test	Yield (Rt0.5)	Yield (Rp0.2)	Tensile (Rm)	T/Y	Elongation (A)
Heat	Test Type	Microstructure	HRBW	Flattening Test	50mm GL	psi	psi	psi	(Rt0.5/Rm)	%
BSM-0584	Heat	Ferrite & Pearlite	76	Pass	Transverse; 38.1mm x WT	41,500	49,100	70,500	0.59	52
						The second secon				

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

- Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product.
- This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng.

Manager of Quality and R&D