

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0589

Product Size:

NPS 20 TRUE80

Hot Expansion

Production Method:

Product Heat Treatment: As-rolled

Production Date: December 5, 2012

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 20 TRUE80 HEAT BSM-0589 (PIPE # LENGTH MASS) 208.91b/ft NDE SMLS NACE MR0175 2012/12 MADE IN CANADA.

BSM-0589	Heat		
Heat	Test Type		
20	NPS		
TRUE80	Thickness	Wall	Product Details
9	Pieces		ls
DRL	Length		
208.90	lb/ft	Mass	
<5	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-[
Pass	٧T	TU)estruct
Pass	ASTM E213	TU	ive Testing
Pass	ASTM E213 ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

	BSM-0589	Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.18	0.21	C		
0.89	0.92	Mn		
0.012	0.014 0.003	P		
0.012 0.004	0.003	S		Chemical Analysis (wt%)
0.27	0.31	Si		Analysis
0.03	0.04	Cr		(wt%)
0.05	0.06	Cu		
0.01	0.01	Mo		
0.02	0.02	Z.		
0.003	0.003	<		
0.003	0.003	П		
0.001	0.001	Nb		
0.0002	0.0002	В		
0.34	,	(IIW)	Œ	
0.34	ı	(CSA)	Œ	

	BSM-0589 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	76	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
46,400	45,900	psi	Yield (Rt0.5)	
46,100	44,400	psi	Yield (Rp0.2)	
68,500	70,000	psi	Tensile (Rm)	
0.68	0.66	(Rt0.5/Rm)	1/4	
55	56	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

√ This certificate represents a quality control system that is compliant with EN 10204;2004 Type 3.1. This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

2012 Dec 21

Manager of Quality and R&D Kenton Dechant, P.Eng.