

## Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc. Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.brichemsteel.com

Production Method: Hot Expansion Product:

Seamless Carbon Steel Pipe

Product Heat Number: BSM-0592

Product Size:

NPS 20 TRUE80

Production Date:

December 7, 2012

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 20 TRUE80 HEAT BSM-0592 (PIPE # LENGTH MASS) 208.91b/ft NDE SMLS NACE MR0175 2012/12 MADE IN CANADA.

BSM-0592	Heat	9	
Heat	Test Type		
20	NPS		
TRUE80	Thickness	Wall	Product Detail
2	Pieces		S
DRL	Length		
208.90	lb/ft	Mass	
5	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-I
Pass	WT	디	Non-Destructive
Pass	ASTM E213	TU	esting
Pass	ASTM E213 ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

	BSM-0592		Heat		
vacuum Degas, Fully Killed	Carrier Donner Trilling Silve	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	D=====================================	Heat	Analysis		
0.22	2	0.21	0		
0.84	0	0.93	Μ'n		
TTO.0	2	0.018	P		
0.005	200	0.001	S		Chemical Analysis (wt%)
0.29	000	0.31	Si		Analysis
0.04	0	0.04	۲ C		(wt%)
0.03	2	0.07	೮		
20.0		0.02	Mo		
0.02	2	0.07	Z.		
0.003		0.003	<		
0.002		0.002	Ħ		
0.001		0.001	Nb		
0.0001		0.0002	В		
0.38		1	(IIW)	Œ	
0.39		ı	(CSA)	CE	

	BSM-0592 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	78	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
46,400	49,300	psi	Yield (Rt0.5)	
46,300	45,600	psi	Yield (Rp0.2)	
70,000	71,500	psi	Tensile (Rm)	
0.66	0.69	(Rt0.5/Rm)	1/4	
53	51	%	Elongation (A)	

Additional Details:

✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the results meet the corresponding requirements.

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

\*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

2012 Dec 21

Manager of Quality and R&D Kenton Dechant, P.Eng.