

Mill Test Certificate

Bri-Steel Manufacturing Inc. 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603 Fax: 001 (780) 469-6986 www.brichemsteel.com

Seamless Carbon Steel Pipe Product Heat Number: BSM-0593 Product Size: NPS 20 TRUE80 Production Date: December 7, 2012

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product:

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 20 TRUE80 HEAT BSM-0593 (PIPE # LENGTH MASS) 208.91b/ft NDE SMLS NACE MR0175 2012/12 MADE IN CANADA.

BSM-0593	Heat		
Heat	Test Type		
20	NPS		
TRUE80	Thickness	Wall	Product Details
7	Pieces		ls
DRL	Length		
208.90	lb/ft	Mass	
<5	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-E
Pass	TW	TU	Non-Destructive Testin
Pass	ASTM E213	TU	esting
Pass	ASTM E213 ASTM E309	ET	
*	٥	HydroTest	
Plain End	Condition	End	

		Т		T
	BSM-0593	Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.22	0.20	C		
0.91	0.92	Mn		
0.91 0.012 0.010	0.011	٩		
0.010	0.003	S		Chemical Analysis (wt%)
0.30	0.31	Si		Analysis
0.03	0.04	ζ.		(wt%)
0.06	0.04	Cu		
0.01	0.01	Mo		
0.02	0.02	Z.		
0.003	0.003	<		
0.003	0.003	Ti		
0.001	0.001	Nb		
0.0001	0.0004	В		
0.39	1	(IIW)	Œ	
0.40	-	(CSA)	CE	

	В	Π		Т
	BSM-0593 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	75	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
46,100	47,200	psi	Yield (Rt0.5)	
46,000	45,500	psi	Yield (Rp0.2)	
68,500	68,500	psi	Tensile (Rm)	
0.67	0.69	(Rt0.5/Rm)	Υ/Τ	
56	54	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the √ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

2012 Dee2 (

Kenton Dechant, P.Eng. Manager of Quality and R&D