

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 **Bri-Steel Manufacturing Inc.**

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0595

Product Size:

NPS 20 TRUE80

Production Date: December 7, 2012

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 20 TRUE80 HEAT BSM-0595 (PIPE # LENGTH MASS) 208.91b/ft NDE SMLS NACE MR0175 2012/12 MADE IN CANADA.

BSM-0595	Heat			
Heat	Test Type			
20	NPS			
TRUE80	Thickness	Wall	Product Details	
6	Pieces		ls	
DRL	Length			
208.90	lb/ft	Mass		
%	μR/hr	Geiger		
<20	Gauss	Res.Mag.		
Pass	insp.	Visual		
Pass	OD		Non-I	
Pass	TW	TU	Non-Destructive Testing	
Pass	ASTM E213	TU	esting	
Pass	ASTM E213 ASTM E309	ET		
*	9	HydroTest		
Plain End	Condition	End		

						Chemical	Chemical Analysis (wt%)	(wt%)									
																CE	Œ
Heat	Steelmaking Method	Analysis	C	Mn	P	S	Si	Cr	Cu	Mo	N:	<	⊐	Nb	В	(IW)	(CSA)
BSM-0595	Blast Furnace; EAF; Ladle Refining;	Heat	0.21	0.92	0.013	0.002	0.33	0.04	0.06	0.01	0.02	0.003	0.002	0.001	0.0001	•	1
	Vacuum Degas; Fully Killed	Product	0.20	0.91	0.015 0.004	0.004	0.27	0.04	0.05	0.01	0.02	0.003	0.003	0.001	1000.0	0.37	0.38

	BSM-0595 Heat	Heat		
	Heat	Test Type	×	
	Ferrite & Pearlite	Microstructure		
	75	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
47,100	49,500	psi	Yield (Rt0.5)	
47,600	47,400	psi	Yield (Rp0.2)	
68,000	70,000	psi	Tensile (Rm)	
0.69	0.71	(Rt0.5/Rm)	Υ/Τ	
55	54	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

√ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

2012 Dec 4

Manager of Quality and R&D Kenton Dechant, P.Eng.