

## Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0603

Product Size:

NPS 20 TRUE80

Production Date:

December 11, 2012

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 20 TRUE80 HEAT BSM-0603 (PIPE # LENGTH MASS) 208.91b/ft NDE SMLS NACE MR0175 2012/12 MADE IN CANADA.

BSM-0603	Heat	:	
Heat	lest Type		
20	NPS		
TRUE80	Thickness	Wall	Product Detail
2	Pieces		ls
DRL	Length		
208.90	lb/ft	Mass	
Ġ	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-D
Pass	WT	T	estructive
Pass	ASTM E213	TU	Testing
Pass	ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

	BSM-0603			Heat			
	Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;		Steelmaking Method			
	Product	Heat	ı	Analysis			
	0.19	0.21		0			
	0.94	0.92		Μn			
	0.013 0.003	0.013		Р			
	0.003	0.002		s			Chemical Analysis (wt%)
	0.28	0.33		S			Analysis
	0.03	0.04		<u>م</u>			(wt%)
	0.06	0.06		Cr			
	0.01	0.01		<u> </u>			
	0.02	0.02		Z.			
	0.003	0.003		<			
	0.003	0.002		_			
	0.001	0.001		25	1001-0		
	0.0001	0.0001	,	D D			
	0.36		10000		כנ	Cr	
0.0.	0.37		1001	(CSA)	(	Cr	

	BSM-0603 Heat	Heat		
	Heat	Test Type	1	
	Ferrite & Pearlite	Microstructure		
	75	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
43,400	44,200	psi	Yield (Rt0.5)	
43,400	39,500	psi	Yield (Rp0.2)	
66,500	73,000	psi	Tensile (Rm)	
0.65	0.61	(Rt0.5/Rm)	Υ/Τ	
54	56	%	Elongation (A)	

## Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product.
- ✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- √ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

\*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.

2013 Jan 7