

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Seamless Carbon Steel Pipe

Production Method:

Hot Expansion

Product Heat Number: BSM-0648

Product Size:

NPS 24 SCH 60

Production Date: January 10, 2013

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 24 SCH 60 HEAT BSM-0648 (PIPE # LENGTH MASS) 238.11b/ft NDE SMLS NACE MR0175 2013/01 MADE IN CANADA.

BSM-0648	Heat		
Heat	Test Type		
24	NPS		
SCH 60	Thickness	Wall	Product Detail
5	Pieces		S
DRL	Length		
238.10	lb/ft	Mass	
~ 5	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-De
Pass	TW	TU	structiv
Pass	ASTM E213 ASTN	T	e Testing
Pass	ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

	BSN			
	BSM-0648	Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.19	0.18	C		
0.91	0.88	Mn		
0.015 0.007	0.010	P		
0.007	0.005	S		Chemical Analysis (wt%)
0.27	0.25	Si		Analysis
0.05	0.03	ç		(wt%)
0.06	0.04	Cu		
0.02	0.01	Mo		
0.03	0.02	N.		
0.003	0.002	<		
0.003	0.002	Ti		
0.001	0.001	Nb		
8000.0	0.0002	В		
0.36	-	(IIW)	3D	
0.37	ı	(CSA)	CE	

				Mechar	Mechanical Properties					
			Hardness		Tension Test	Yield (Rt0.5)	Yield (Rp0.2)	Tensile (Rm)	Τ/Υ	Elongation (A
Heat	Test Type	Microstructure	HRBW	Flattening Test	50mm GL	psi	psi	psi	(Rt0.5/Rm)	%
BSM-0648 Heat	Heat	Ferrite & Pearlite	76	Pass	Transverse; 38.1mm x WT	45,200	42,300	69,500	0.65	57
					Longitudinal; 38.1mm x WT	48,100	48,700	68,500	0.70	55

Additional Details:

Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

results meet the corresponding requirements.

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

√ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.

2013 Jan 25