

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc. Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.brichemsteel.com

Production Date:

January 10, 2013

Seamless Carbon Steel Pipe **Product Heat Number:** BSM-0652 Product Size: NPS 24 SCH 60

Product:

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 24 SCH 60 HEAT BSM-0652 (PIPE # LENGTH MASS) 238.11b/ft NDE SMLS NACE MR0175 2013/01 MADE IN CANADA.

BSM-0652	-		
Heat	Test Type		
24	NPS		71
SCH 60	Thickness	Wall	Product Details
1	Pieces		S
DRL	Length		
238.10	lb/ft	Mass	
S	μR/hr	Geiger	
<20	Gauss	Res.Mag.	9
Pass	Insp.	Visual	
Pass	OD		Non-D
Pass	TW	T	Non-Destructive
Pass	ASTM E213	TU	e Testing
Pass	ASTM E213 ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

000	BSM-0652			
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.19	0.20	C		
0.92	0.93	Mn		
0.011	0.014	P		
0.011 0.004	0.005	S		Chemical Analysis (wt%)
0.29	0.32	Si		l Analysis
0.04	0.06	Cr		(wt%)
0.05	0.05	Cu		
0.03	0.01	Mo		
0.02	0.02	N.		
0.003	0.003	<		
0.002	0.002	Ţ		
0.001	0.001	Nb		
0.0002	0.0003	В		
0.36	1	(IIW)	Œ	
0.37	1	(CSA)	CE	

	BSM-(Heat		
	BSM-0652			
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	76	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
47,300	45,200	psi	Yield (Rt0.5)	
47,900	44,800	psi	Yield (Rp0.2)	
69,500	69,000	psi	Tensile (Rm)	
0.68	0.66	(Rt0.5/Rm)	T/Y	
58	54	%	Elongation (A)	

Additional Details:

Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the results meet the corresponding requirements. ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

√ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. 2013 Jan 30

Manager of Quality and R&D