

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 **Bri-Steel Manufacturing Inc.**

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.brichemsteel.com

Seamless Carbon Steel Pipe

Product Heat Number: BSM-0674

Product Size:

NPS 24 SCH 160

Production Date: January 30, 2013

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 24 SCH 160 HEAT BSM-0674 (PIPE # LENGTH MASS) 541.91b/ft NDE SMLS NACE MR0175 2013/01 MADE IN CANADA.

BSM-0674	Heat		
Heat	Test Type		
24	NPS		_
SCH 160	Thickness	Wall	Product Detail
0	Pieces		S
DRL	Length		
541.90	lb/ft	Mass	
ک	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	insp.	Visual	
Pass	OD		Non-D
Pass	WT	듸	estructive.
Pass	ASTM E213	TU	Testing
Pass	ASTM E309	ET	
1		HydroTest	
Plain End	Condition	End	

0	RSM-C	Heat		
BSM-0674		at		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method	and the second s	
Product	Heat	Analysis		
0.19	0.19	С		
0.89	0.88	Mn		
0.016	0.013	ק		
0.89 0.016 0.004 0.30	0.013 0.002 0.31	S		Chemical
0.30	0.31	Si		Chemical Analysis (wt%)
0.04	0.06	Ç		(wt%)
0.06	0.05	Cu		
0.01	0.01	Mo		
0.03	0.02	Z:		
0.003	0.003	<		
0.003	0.003	T		
0.001	0.001	Nb		
0.0004	0.0001	В		
0.35	-	(IIW)	J.	
0.36	t)	(CSA)	CE	

	BSM-0674 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	74	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 19.1mm x WT	Transverse; 19.1mm x WT	50mm GL	Tension Test	Mechanical Properties
44,400	58,500	psi	Yield (Rt0.5)	
43,200	55,000	psi	Yield (Rp0.2)	
74,500	75,500	psi	Tensile (Rm)	
0.60	0.77	(Rt0.5/Rm)	Τ/Υ	
48	44	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng.

201376615

Manager of Quality and R&D