

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0683

Product Size:

NPS 24 STD

Production Date: February 5, 2013

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG <API> 5L-0898 API 5L GR B PSL1 ASTM/ASME A/5A106 GR B/C A/SA53 GR B NPS 24 STD HEAT BSM-0685 (PIPE # LENGTH MASS) 94.62Ib/ft NDE 740 PSI SMLS NACE MR0175 2013/02 MADE IN CANADA.

BSM-0683	Heat		
Heat	Test Type		
24	NPS		
STD	Thickness	Wall	Product Detail
26	Pieces		ls
DRL	Length		
94.62	lb/ft	Mass	
Ġ	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-C
Pass	WT	디	Destructive
Pass	ASTM E213	TU	Testing
Pass	ASTM E309	ET	
Pass	740 psi/5s	HydroTest	
37.5° Bevel	5s Condition	End	

	BSM-0683			
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.20	0.19	С		
0.89	0.86	Mn		
0.007	0.008	P		
0.007 0.008 0.24	0.005	S		Chemical Analysis (wt%)
0.24	0.24	Si		Analysis
0.02	0.03	೪		(wt%)
0.09	0.08	Cu		
0.02	0.02	Mo		
0.04	0.05	<u>Z</u>		
0.002	t	<		
0.001	1	П		
0.001	,	Nb		
0.0002	0.0003	В		
0.37		(IIW)	CE	
0.37	-	(CSA)	CE	

	BSM-06	Heat			
	BSM-0683 Heat	Test			
	leat	Test Type			
	Ferrite & Pearlite	Microstructure			
	77	HRBW	Hardness		
	Pass	Flattening Test		Mechan	
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties	
48,500	46,200	psi	Yield (Rt0.5)		
48,400	46,000	psi	Yield (Rp0.2)		
71,000	72,000	psi	Tensile (Rm)		
0.68	0.64	(Rt0.5/Rm)	۲/۲		
45	42	%	Elongation (A)		

Additional Details:

and that the results meet the corresponding requirements. \checkmark We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements,

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

Mill Test Certificate approved by:

2013 Feb 11

Manager of Quality and R&D Kenton Dechant, P.Eng.