

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0684

Production Date: February 5, 2013

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Size:

NPS 24 SCH 160

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 24 SCH 160 HEAT BSM-0684 (PIPE # LENGTH MASS) 541.91b/ft NDE SMLS NACE MR0175 2013/02 MADE IN CANADA.

BSM-0684 Heat 24	Heat Test Type NPS		
4 SCH 160	S Thickness		Product Detail
2	Pieces		S
DRL	Length		
541.90	lb/ft	Mass	
<5	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-D
Pass	WT	TU	estructive T
Pass	ASTM E213	TU	esting
Pass	ASTM E309	ET	
-		HydroTest	
Plain End	Condition	End	

5	D.			
BSM-0684		Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.20	0.20	C		
0.90	0.90	Mn		
0.015	0.017	Р		
0.90 0.015 0.004 0.29	0.002	S		Chemical
0.29	0.34	Si		Chemical Analysis (wt%)
0.05	0.05	Cr		(wt%)
0.05	0.05	Cu		
0.01	0.00	Mo		
0.03	0.02	Z.		
0.003	0.003	<		
0.003	0.003	П		
0.001	0.001	Nb		
0.0002	0.0001	В		
0.37		(IW)	CE	
0.38	1	(CSA)	CE	

	_	_	_	
	BSM-0684 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure	00 00	
	74	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal; 19.1mm x WT	Transverse; 19.1mm x WT	50mm GL	Tension Test	Mechanical Properties
51,000	46,200	psi	Yield (Rt0.5)	
63,500	46,800	psi	Yield (Rp0.2)	
72,000	72,500	psi	Tensile (Rm)	
0.71	0.64	(Rt0.5/Rm)	Υ/Τ	
51	45	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

✓ No weld repairs have been performed on this product.

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.

201312618