



Mill Test Certificate

Product: **Seamless Carbon Steel Pipe** Product Heat Number: **BSM-0694** Product Size: **NPS 24 TRUE40** Production Date: **February 7, 2013**

Production Method: **Hot Expansion** Product Heat Treatment: **As-rolled**

Product Standards: **ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SAA106-2011 Grade B/C NDE, A/SAS3-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010**

Product Markings: **.BRI-STEEL MFG <API> 5L-0898 API 5L GR B PSL1 ASTM/ASME A/SAA106 GR B/C A/SAS3 GR B NPS 24 TRUE40 HEAT BSM-0694 (PIPE # LENGTH MASS) 171.2lb/ft NDE 1370 PSI SMLS NACE MR0175 2013/02 MADE IN CANADA.**

Product Details				Non-Destructive Testing											
Heat	Test Type	NPS	Wall Thickness	Pieces	Length	Mass	Gelger	Res. Mag.	Visual	OD	UT	UT	ET	HydroTest	End
BSM-0694	Heat	24	TRUE40	7	DRL	171.20	µR/hr	Gauss	Insp.	Pass	Pass	Pass	Pass	1370 psi/5s	Condition
							<5	<20	Pass	Pass	Pass	Pass	Pass	Pass	Plain End

Chemical Analysis (wt%)																	
Heat	Steelmaking Method	Analysis	C	Mn	P	S	Si	Cr	Cu	Mo	Ni	V	Ti	Nb	B	CE	CE
BSM-0694	Blast Furnace; EAF; Ladle Refining; Vacuum Degass; Fully Killed	Heat	0.20	0.99	0.015	0.003	0.30	0.05	0.06	0.01	0.03	0.003	0.002	0.001	0.0001	-	-
		Product	0.20	0.93	0.018	0.006	0.30	0.05	0.05	0.01	0.03	0.003	0.002	0.001	0.0002	0.37	0.38

Mechanical Properties														
Heat	Test Type	Microstructure	Hardness	Flattening Test	Tension Test					Yield (Rt0.5)	Yield (Rp0.2)	Tensile (Rm)	V/T	Elongation (A)
					HRBW	50mm GL	psi	psi	psi					
BSM-0694	Heat	Ferrite & Pearlite	80	Pass	Transverse; 38.1mm x WT	45,700	52,500	74,000	72,500	74,000	0.62	0.72	54	
					Longitudinal; 38.1mm x WT	52,500	52,500	72,500	72,500	72,500	0.72	0.72	52	

Additional Details:

- ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SAA106-2011, A/SAS3-2012 and the purchase order requirements, and that the results meet the corresponding requirements.
- ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service, and NACE MR0103-2010 Section 2.1.
- ✓ No weld repairs have been performed on this product.
- ✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- ✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

[Signature]
2013 Feb 15

Kenton Dechant, P.Eng.
Manager of Quality and R&D