

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0701

NPS 24 SCH 160

Production Date:

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Size:

February 12, 2013

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 24 SCH 160 HEAT BSM-0701 (PIPE # LENGTH MASS) 541.91b/ft NDE SMLS NACE MR0175 2013/02 MADE IN CANADA.

BSM-0701	Heat		
Heat	Test Type		
24	NPS		
SCH 160	Thickness	Wall	Product Detail
6	Pieces		S
DRL	Length		
541.90	lb/ft	Mass	
<5	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-[
Pass	WT	TU	Non-Destructive Testing
Pass	ASTM E213	TU	Testing
Pass	ASTM E213 ASTM E309	ET	
-		HydroTest	
Plain End	Condition	End	

BSM-0701 Blase Latitiace, Ent. / Fadie IV	Riast Furnace: FAF: I adla Rafining:	Heat Steelmaking Method		
ally Killed Product	fining; Heat	Analysis		
0.19	0.20	C		
0.19 0.89 0.016 0.004 0.29	0.88	Mn		
0.016	0.015	P		
0.004	0.004	S		Chemical Analysis (wt%)
0.29	0.32	Si		Analysis
0.04	0.04	Cr		(wt%)
0.05	0.05	Cu		
0.01	0.02	Mo		
0.02	0.02	N.		
0.003	0.004	<		
0.003	0.003	Ti		
0.001	0.001	Nb		
0.0002	0.0002	В		
0.35	1	(WII)	Œ	
0.36	1	(CSA)	CE	

	BSM-0701 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	78	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 19.1mm x WT	Transverse; 19.1mm x WT	50mm GL	Tension Test	Mechanical Properties
	41,500	psi	Yield (Rt0.5)	
35,200	41,500	psi	Yield (Rp0.2)	
74,500	78,000	psi	Tensile (Rm)	
0.48	0.53	(Rt0.5/Rm)	۲/۲	
45	32	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.