

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 **Bri-Steel Manufacturing Inc.**

Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0702

Product Size:

NPS 24 SCH 160

Production Date: February 12, 2013

Production Method: **Hot Expansion**

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

1	_		-		-	-		_	
	BSM-0702		Heat				BSM-0702	Heat	
	Vacuum	Blast Furnace	Steeln				Heat	Test Type	
	Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method				24	NPS	
	illed	efining;	ď				SCH 160	Thickness	WAL
	Product	Heat	Analysis				6	Pieces	
	0.19	0.20	C				DRL	Len	
	0.88	0.90	Mn				٣	Length	
	0.014 0.005	0.017	P				541.90	lb/ft	IVIdSS
	0.005	0.002	S		Chemical Analysis (wt%)		Ġ.	μR/hr	Geigei
	0.29	0.34	Si		Analysis		<20	Gauss	Kes.IVIdg.
	0.05	0.05	Cr		wt%)		0	ISS	Vide.
	0.01	0.05	Cu				Pass	Insp.	VISUAI
	0.01	0.01	Mo				Pass	OD	
	0.02	0.02	N:				Pass	WT	
	0.003	0.003	<				S		
	0.003	0.003	1				Pass	3TM E213	_
	0.001	0.001	Nb				Pass	ASTM E213 ASTM E309	п
	0.0002 0.35	0.0001	В					19	Hydrolest
	0.35	,	(IIW)	CE			7	C	
Ì	0.36	1	(CSA)	CE			Plain End	Condition	End

		1		_
	BSM-0702 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	73	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal; 12.7mm x WT	Transverse; 12.7mm x WT	50mm GL	Tension Test	Mechanical Properties
36,800	49,100	psi	Yield (Rt0.5)	
36,100	47,300	psi	Yield (Rp0.2)	
70,000	72,500	psi	Tensile (Rm)	
0.53	0.68	(Rt0.5/Rm)	1/4	
53	46	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.

2013 Feb 20