

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0717

Product Size:

NPS 20 STD

Production Date:

February 18, 2013

Production Method: **Hot Expansion**

Product Markings:

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

.BRI-STEEL MFG <API> 51-0898 API 51 GR B PSL1 ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 20 STD 0.375 inchWT HEAT BSM-0717 (PIPE # LENGTH MASS) 78.6Ib/ft NDE 910 PSI SMLS NACE MR0175 2013/02 MADE IN CANADA.

Insp. OD	TW	ASTM E2	E213 ASTM
			_
Visual		TU	
	No	Non-Destructive	Non-Destructive Testing
	Visual	Non-Destr	Non-Destructive Testing

į į	BSN			
	RSM-0717	Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.21	0.19	0		
0.87	0.86	Μ		
0.010	0.009	P		
0.017	0.016	S		Chemical Analysis (wt%)
0.22	0.22	Si		Analysis
0.05	0.05	Cr		(wt%)
0.10	0.10	Cn		
0.01	0.01	Mo		
0.07	0.07	Z.		
0.002	1	<		
0.001	•	П		
0.001	ı	Nb		
0.0002	0.0003	В		
0.38	-	(IIW)	CE	
0.38	•	(CSA)	CE	

		Т		Г
	BSM-0717 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	76	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
44,000	45,600	psi	Yield (Rt0.5)	-
43,700	45,500	psi	Yield (Rp0.2)	
71,000	71,500	psi	Tensile (Rm)	
0.62	0.64	(Rt0.5/Rm)	Τ/Υ	
39	37	%	Elongation (A)	

Additional Details:

and that the results meet the corresponding requirements. Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1 This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

√ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. √ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

Mill Test Certificate approved by:

2013 Feb 22

Manager of Quality and R&D Kenton Dechant, P.Eng.