

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 **Bri-Steel Manufacturing Inc.**

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Product Size: NPS 20 TRUE80 Production Date: February 21, 2013

Production Method: Hot Expansion Product Heat Treatment: As-rolled

ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

.BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 20 TRUE80 1.031 inchWT HEAT BSM-0731 (PIPE # LENGTH MASS) 208.9Ib/ft NDE SMLS NACE MR0175 2013/02 MADE IN CANADA.

Product Markings:

Product Standards:

Product:

Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0731

BSM-0731 Heat NPS 20 TRUE80 1.031 in.WT 2 DRL 208.90 <	Heat Test Type Product Size Pieces Length lb/ft μR	Mass	Product Details
	t Type		
	Product Size		Product Detail
2	Pieces		S
DRL	Length		
208.90	lb/ft	Mass	
Ġ	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-E
Pass	TW	UT	estructive 7
Pass	ASTM E213	TU	esting
Pass	ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

						Chemical Analysis (wt%)	Analysis	(wt%)					3				V
																Œ	Œ
Heat	Steelmaking Method	Analysis	С	Mn	P	S	Si	Ç	Cu	Mo	Z.	<	∄	N _b	В	(IW)	(CSA)
BSM-0731	Blast Furnace; EAF; Ladle Refining;	Heat	0.18	0.88	0.010 0.005	0.005	0.25	0.03	0.04	0.01	0.02	0.002	0.002	0.001	0.0002	ı	1
0.0	Vacuum Degas; Fully Killed	Product	0.20	0.95	0.95 0.015 0.002	0.002	0.33	0.01	0.05	0.01	0.05	0.003	0.004	0.001	0.0002	0.37	0.38

	BSM-0731	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	76	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
47,200	48,800	psi	Yield (Rt0.5)	
47,300	48,800	psi	Yield (Rp0.2)	
72,000	73,000	psi	Tensile (Rm)	
0.66	0.67	(Rt0.5/Rm)	1/7	
61	56	%	Elongation (A)	

Additional Details:

Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the results meet the corresponding requirements. We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

*Note that this product was hydrotested to 1000 psi for 5 seconds

Mill Test Certificate approved by:

Kenton Dechant, P.Eng.

Manager of Quality and R&D

2013 Mary