

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 **Bri-Steel Manufacturing Inc.**

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986 www.brichemsteel.com

Product Size: NPS 20 TRUE80 Production Date: February 21, 2013

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product:

Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0733

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 20 TRUE80 1.031 inchWT HEAT BSM-0733 (PIPE # LENGTH MASS) 208.9Ib/ft NDE SMLS NACE MR0175 2013/02 MADE IN CANADA.

BSM-0733	Heat		
Heat	Test Type		
NPS 20 TRUE80 1.031 in.WT	Product Size		Product Detail
1	Pieces		5
DRL	Length		
208.90	lb/ft	Mass	
<5	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-E
Pass	TW	TU	estructive T
Pass	ASTM E213	TU	esting
Pass	ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

BSM-0733		Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.19	0.20	C		
0.93	0.94	Mn		
0.014	0.013	Р		
0.93 0.014 0.004 0.31 0.04	0.013 0.003	S		Chemical
0.31	0.31	Si		Chemical Analysis (wt%)
0.04	0.04	Cr		(wt%)
0.06	0.05	Cu		
0.02	0.02	Mo		
0.02	0.02	<u>Z</u> .		
0.003	0.002	<		
0.003	0.002	=!		
0.001	0.001	Nb		
0.0002	0.0003	В		
0.36	1	(IIW)	CE	
0.37		(CSA)	CE	

	_		_	T
	BSM-0733 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	77	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
	46,900	psi	Yield (Rt0.5)	
48,200	44,100	psi	Yield (Rp0.2)	
71,000	72,000	psi	Tensile (Rm)	
0.66	0.65	(Rt0.5/Rm)	Υ/Τ	
58	54	%	Elongation (A)	

Additional Details:

Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the results meet the corresponding requirements. ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

*Note that this product was hydrotested to 1000 psi for 5 seconds

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. 2013 Merry

Manager of Quality and R&D