

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Seamless Carbon Steel Pipe

Product Heat Number: BSM-0737

NPS 24 STD

Production Date:

February 25, 2013

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Size:

Product Standards: ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG <API> 51-0898 API 5L GR B PSL1 ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 24 STD 0.375 InchWT HEAT BSM-0737 (PIPE # LENGTH MASS) 94.62lb/ft NDE 740 PSI SMLS NACE MR0175 2013/02 MADE IN CANADA.

BSM-0737	Heat		
Heat	Test Type		
NPS 24 STD 0.375 in.WT	Product Size		Product Detail
4	Pieces		ls
DRL	Length		
94.62	lb/ft	Mass	
\$	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-I
Pass	WT	TU	Destructive 1
Pass	ASTM E213	TU	esting
Pass	ASTM E309	ET	
Pass	740 psi/5s	HydroTest	
37.5° Bevel	Condition	End	

		1	_	Т
	BSM-0737	Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.20	0.19	0		
0.86	0.87	Mn		
0.014	0.012	P	8	
0.010	0.009	S		Chemical Analysis (wt%)
0.26	0.25	S:		Analysis
0.04	0.03	ç.		(wt%)
0.09	0.08	5		
0.02	0.02	Mo		
0.04	0.04	<u>z</u>		
0.003		<		
0.002		∄		
0.001	1	Мb		
0.0003	0.0004	В		
0.36	ı	(IIW)	CE	
0.37	1	(CSA)	Œ	

	BSM-0737 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	80	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
48,900	54,000	psi	Yield (Rt0.5)	
48,700	52,500	psi	Yield (Rp0.2)	
71,000	75,000	psi	Tensile (Rm)	
0.69	0.72	(Rt0.5/Rm)	Τ/Υ	
41	39	%	Elongation (A)	

Additional Details:

- and that the results meet the corresponding requirements. Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product.
- This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. Manager of Quality and R&D