

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0739

Product Size:

NPS 24 STD

Production Date:

February 25, 2013

Production Method: Hot Expansion

Product Standards:

Product Heat Treatment: As-rolled

Product Markings: .BRI-STEEL MFG <API> 51-0898 API 51 GR B PSL1 ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 24 STD 0.375 inchWT HEAT BSM-0739 (PIPE # LENGTH MASS) 94.62lb/ft NDE 740 PSI SMLS NACE MR0175 2013/02 MADE IN CANADA.

ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

| BSM-0739 | Heat | | |
|------------------------|--------------|-----------|----------------|
| Heat | Test Type | ľ | |
| NPS 24 STD 0.375 in.WT | Product Size | | Product Detail |
| 6 | Pieces | | S |
| DRL | Length | | |
| 94.62 | lb/ft | Mass | |
| Ġ | μR/hr | Geiger | |
| <20 | Gauss | Res.Mag. | |
| Pass | Insp. | Visual | |
| Pass | OD | | Non-E |
| Pass | WT | TU | estructive T |
| Pass | ASTM E213 | TU | e Testing |
| Pass | ASTM E309 | ET | |
| Pass | 740 psi/5s | HydroTest | |
| 37.5° Bevel | Condition | End | |

| BSM-0739 | | Heat | | | The second secon | | | |
|----------------------------|-------------------------------------|-------|--------------------|--------|--|--|-------------------------|--|
| Vacuum Degas; Fully Killed | Blast Furnace; EAF; Ladle Refining; | | Steelmaking Method | | | | | |
| Product | Heat | | Analysis | | | | | |
| 0.21 | 0.19 | | 0 | | | | | |
| 0.87 | 0.84 | | Z n | 200000 | No. | | | |
| 0.009 | 0.009 | | ס | | | | | |
| 0.008 | 0.007 | | S | | | | Chemical | |
| 0.25 | 0.24 | | S | | | | Chemical Analysis (wt%) | |
| 0.06 | 0.06 | | Ç | | | | (wt%) | |
| 0.10 | 0.08 | | Cu | | | | | |
| 0.01 | 0.01 | | <u>S</u> | | | | | |
| 0.06 | 0.05 | | Z. | | | | | |
| 0.002 | | | < | | | | | |
| 0.002 | 1 | | =! | | | | | |
| 0.001 | | | 25 | | | | | |
| 0.0002 | 2000.0 | , | ס | | | | | |
| 85.0 | ı | 1 | | 6 | Cr. | | | |
| 0.39 | 1 | 10001 | (CSA) | כה | 7 | | | |

| | BSM-0739 Heat | Heat | : | |
|---------------------------|-------------------------|-----------------|----------------|-----------------------|
| | Heat | lest lype | l | |
| | Ferrite & Pearlite | Microstructure | | |
| | 77 | HRBW | Hardness | |
| | Pass | Flattening Test | | Mechar |
| Longitudinal; 38.1mm x WT | Transverse; 38.1mm x WT | 50mm GL | Tension Test | Mechanical Properties |
| 46,600 | 51,500 | psi | Yield (Rt0.5) | |
| 46,000 | 51,500 | psi | Yield (Rp0.2) | |
| 74,000 | 75,500 | psi | Tensile (Rm) | |
| 0.63 | 0.68 | (Rt0.5/Rm) | 1/4 | |
| 39 | 43 | % | Elongation (A) | |

Additional Details:

and that the results meet the corresponding requirements. Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1 ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

 \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

2013Feb-28

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. Manager of Quality and R&D