

## Mill Test Certificate

**Bri-Steel Manufacturing Inc.** 

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0743

NPS 24 STD

February 25, 2013

Production Method: Hot Expansion

Product Markings:

Product Size:

Production Date:

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

.BRI-STEEL MFG <API> 51-0898 API 51 GR B PSL1 ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 24 STD 0.375 inchWT HEAT BSM-0743 (PIPE # LENGTH MASS) 94.621b/ft NDE 740 PSI SMLS NACE MR0175 2013/02 MADE IN CANADA.

BSM-0743	Heat		
43 Heat	Test Type		
NPS 24 STD 0.375 in.WT	Product Size		Product Detail
1	Pieces		ls
DRL	Length		
94.62	lb/ft	Mass	
ŝ	μR/hr	Geiger	
<20	Gauss	r Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-I
Pass	WT	TU	Destructive T
Pass	ASTM E213	TU	Testing
Pass	ASTM E309	ET	
Pass	740 psi/5s	HydroTest	
37.5° Bevel	Condition	End	

Ti Nb B (IIW) (CSA)
Cr Cu Mo Ni V Ti Nb B (IIW)  0.05 0.10 0.01 0.06 0.0005 - 0.
Cu Mo Ni V Ti Nb B (IIW) 5 0.10 0.01 0.06 0.0005 - 6 0.11 0.01 0.06 0.004 0.002 0.001 0.0003 0.37
Cu Mo Ni V Ti Nb B (IIW) 5 0.10 0.01 0.06 0.0005 - 6 0.11 0.01 0.06 0.004 0.002 0.001 0.0003 0.37
Mo Ni V Ti Nb B (IIW) 1 0.01 0.06 0.0005 - 0.001 0.060 0.37
Ni V Ti Nb B (IIW)  0.06 0.0005 - 0.0005 - 0.006  0.06 0.004 0.002 0.001 0.0003 0.37
V Ti Nb B (IIW) 0.0005 0.0004 0.002 0.001 0.0003 0.37
Ti Nb B (IIW)  0.0005 - 0.001 0.0003 0.37
Nb B (IIW) - 0.0005 - 0.0001 0.0003 0.37
CE (IIW) 0.0005 - 0.0003 0.37
CE (IIW)
CE (CSA)

	BSM-0743 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	75	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
46,100	42,800	psi	Yield (Rt0.5)	
46,100	41,600	psi	Yield (Rp0.2)	
72,000	72,500	psi	Tensile (Rm)	
0.64	0.59	(Rt0.5/Rm)	1/4	
41	45	%	Elongation (A)	

Additional Details:

and that the results meet the corresponding requirements. Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

√ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. √ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

Mill Test Certificate approved by:

Kenton Dechant, P.Eng.

2013 Feb 28

Manager of Quality and R&D