

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0754

NPS 18 STD

Production Date: March 5, 2013

Product Size:

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MEG <API> 51-0898 API 51 GR B PSL1 ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 18 STD 0.375 inchWT HEAT BSM-0754 (PIPE # LENGTH MASS) 70.59lb/ft NDE 1030 PSI SMLS NACE MR0175 2013/03 MADE IN CANADA.

BSM-0754	Heat		
Heat	Test Type		
NPS 18 STD 0.375 in.WT	Product Size		Product Details
10	Pieces		S
DRL	Length		
70.59	lb/ft	Mass	
<5	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-E
Pass	TW.	UT	estructive
Pass	ASTM E213	TU	Testing
Pass	ASTM E309	ET	
Pass	M E309 1030 psi/5s	HydroTest	
37.5° Bevel	Condition	End	

						Chemical Analysis (wt%)	Analysis	(wt%)									
																CE	CE
Heat	Steelmaking Method	Analysis	С	Mn	Р	S	<u>s:</u>	ر	Cu	ŏ o	<u>z</u> .	<	=	В	В	(EW)	(CSA)
RSM-0754	Blast Furnace; EAF; Ladle Refining;	Heat	0.19	0.88	0.007	0.004	0.23	0.05	0.06	0.04	0.03	r	1	,	0.0004	3	1
0,01	Vacuum Degas; Fully Killed	Product	0.21	0.90	0.008	0.006	0.25	0.06	0.06	0.04	0.03	0.002	0.002	0.001	0.0003	0.39	0.40

	BSM-0754 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	76	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
47,200	46,000	psi	Yield (Rt0.5)	
47,100	45,300	psi	Yield (Rp0.2)	
72,000	73,500	psi	Tensile (Rm)	
0.66	0.63	(Rt0.5/Rm)	1/7	
43	39	%	Elongation (A)	

Additional Details:

and that the results meet the corresponding requirements. Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

✓ No weld repairs have been performed on this product.

✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

Mill Test Certificate approved by:

2013 Mar 13

Manager of Quality and R&D Kenton Dechant, P.Eng.