

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc. Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0764

NPS 18 STD

Production Date:

March 7, 2013

Production Method: **Hot Expansion**

Product Markings:

Product Standards:

Product Heat Treatment: As-rolled

Product Size:

ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

.BRI-STEEL MFG <API> 5L-0898 API 5L GR B PSL1 ASTM/ASME A/5A106 GR B/C A/5A53 GR B NPS 18 STD 0.375 inchWT HEAT BSM-0764 (PIPE # LENGTH MASS) 70.59lb/ft NDE 1030 PSI SMLS NACE MR0175 2013/03 MADE IN CANADA.

BSM-0764 Test Type Heat NPS 18 STD 0.375 in.WT Product Size Product Details Pieces 4 Length DRL 70.59 Mass lb/ft Geiger µR/hr ŝ Res.Mag. Gauss <20 Visual Insp. Pass Pass 90 Non-Destructive Testing Pass ¥ c ASTM E213 ASTM E309 1030 psi/5s Pass S Pass Ξ HydroTest Pass 37.5° Bevel Condition End

| | BSM-0764 | | | |
|----------------------------|-------------------------------------|--------------------|----|-------------------------|
| Vacuum Degas; Fully Killed | Blast Furnace; EAF; Ladle Refining; | Steelmaking Method | | |
| Product | Heat | Analysis | | |
| 0.21 | 0.19 | C | | |
| 0.93 | 0.91 | Mn | | |
| 0.93 0.007 | 0.008 | P | | |
| 0.005 | 0.003 | S | | Chemical |
| 0.23 | 0.22 | Si | | Chemical Analysis (wt%) |
| 0.03 | 0.05 | Ç | | (wt%) |
| 0.07 | 0.06 | Cu | | |
| 0.01 | 0.01 | Mo | | |
| 0.03 | 0.03 | N. | | |
| 0.002 | ı | < | | |
| 0.001 | ı | ∄ | | |
| 0.001 | 1 | Nb | | |
| 0.0002 | 0.0004 | œ | | |
| 0.38 | | (IW) | CE | |
| 0.39 | ı | (CSA) | CE | |

| | BSM-0764 Heat | Heat | | |
|---------------------------|-------------------------|-----------------|----------------|-----------------------|
| | Heat | Test Type | | |
| | Ferrite & Pearlite | Microstructure | | |
| | 78 | HRBW | Hardness | |
| | Pass | Flattening Test | | Mechar |
| Longitudinal; 38.1mm x WT | Transverse; 38.1mm x WT | 50mm GL | Tension Test | Mechanical Properties |
| 45,700 | 42,600 | psi | Yield (Rt0.5) | |
| 45,600 | 41,700 | psi | Yield (Rp0.2) | |
| 71,500 | 72,000 | psi | Tensile (Rm) | |
| 0.64 | 0.59 | (Rt0.5/Rm) | Υ/Τ | |
| 43 | 42 | % | Elongation (A) | |

Additional Details:

and that the results meet the corresponding requirements. Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

 \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

Mill Test Certificate approved by:

2013 Mar 13

Manager of Quality and R&D Kenton Dechant, P.Eng.