

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0768

NPS 18 STD

Production Date:

March 12, 2013

Production Method: Hot Expansion

Product Markings:

Product Heat Treatment: As-rolled

Product Size:

Product Standards: ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

.BRI-STEEL MFG <API> 51-0898 API 51 GR B PSL1 ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 18 STD 0.375 inchWT HEAT BSM-0768 (PIPE # LENGTH MASS) 70.591b/ft NDE 1030 PSI SMLS NACE MR0175 2013/03 MADE IN CANADA.

BSM-0768	Heat	:		
Heat	Test Type			
NPS 18 STD 0.375 in.WT	Product Size		Product Detail:	
15	Pieces		S	
DRL	Length			
70.59	lb/ft	Mass		
Ġ	μR/hr	Geiger		
<20	Gauss	Res.Mag.		
Pass	Insp.	Visual		
Pass	OD		Non-E	
Pass	WT	TU	estructive T	
Pass	ASTM E213 A	T	esting	
Pass	NTS	四		
Pass	1 E309 1030 psi/5s	HydroTest		
37.5° Bevel	Condition	End		

BSM-0768		Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.21	0.19	C		
0.92	0.91	Mn		
0.007	0.008	P		
0.007 0.004 (0.003	S		Chemical Analysis (wt%)
0.23	0.22	Si		Analysis
0.03	0.05	Cr		(wt%)
0.06	0.06	೮		
0.01	0.01	Mo		
0.03	0.03	Z.		
0.003	t	<		
0.001	ı	ī		
0.002	1	Nb		
0.0003	0.0004	В		
0.38		(IIW)	Œ	
0.39		(CSA)	CE	

	BSM-0768 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	74	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
45,800	44,000	psi	Yield (Rt0.5)	
45,600	42,700	psi	Yield (Rp0.2)	
72,000	71,500	psi	Tensile (Rm)	
0.64	0.62	(Rt0.5/Rm)	Τ/Υ	
46	39	%	Elongation (A)	

Additional Details:

and that the results meet the corresponding requirements. Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1 This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

 \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng

BISMAC

Manager of Quality and R&D