

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 124 Tel: 001 (780) 469-6603 Fax: 001 (780) 469-6986

www.brichemsteel.com

NPS 14 STD Production Date: March 26, 2013

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product:

Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0789

Product Size:

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 14 STD 0.375 inchWT HEAT BSM-0789 (PIPE # LENGTH MASS) 54.571b/ft NDE SMLS NACE MR0175 2013/03 MADE IN CANADA.

BSM-0789 Heat	Heat Test Type		
NPS 14 STD 0.375 in.WT	Product Size		Product Detail
16	Pieces		S
DRL	Length		
54.57	lb/ft	Mass	
<5	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-D
Pass	WT	TI	estructive T
Pass	ASTM E213	TU	esting
Pass	ASTM E309	ET	
		HydroTest	
37.5° Bevel	Condition	End	

						Chemical	Chemical Analysis (wt%)	(wt%)									
																CE	CE
Heat	Steelmaking Method	Analysis	C	Mn	Р	S	Si	Cr	Си	Mo	N:	<	Ti	Nb	В	(IIW)	(CSA)
RSM-0789	Blast Furnace; EAF; Ladle Refining;	Heat	0.20	0.89	0.013	0.004	0.24	0.04	0.05	0.01	0.03	£	e.	r	0.0002	t	r
00,41-07	Vacuum Degas; Fully Killed	Product	0.20	0.90	0.012	0.005	0.24	0.04	0.06	0.01	0.03	0.002	0.001	0.001	0.0002	0.37	0.37

	BSM-0789 Heat	Heat			
	Heat	Test Type			
	Ferrite & Pearlite	Microstructure			
	76	HRBW	Hardness		
	Pass	Flattening Test		Mechar	
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties	
44,800	44,400	psi	Yield (Rt0.5)		
44,800	42,500	psi	Yield (Rp0.2)		
71,500	72,000	psi	Tensile (Rm)		
0.63	0.62	(Rt0.5/Rm)	Τ/Υ		
42	43	%	Elongation (A)		

Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- ✓ No weld repairs have been performed on this product.
- ✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- ✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. Manager of Quality and R&D

2013Apr1