

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 **Bri-Steel Manufacturing Inc.**

Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Production Method:

Product Heat Number:

BSM-0791

Product Size:

NPS 14 STD

Production Date: March 26, 2013

Hot Expansion Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 14 STD 0.375 inchWT HEAT BSM-0791 (PIPE # LENGTH MASS) 54.571b/ft NDE SMLS NACE MR0175 2013/03 MADE IN CANADA.

BSM-0791	Heat		
Heat	Test Type		
NPS 14 STD 0.375 in.WT	Product Size		Product Detail
7	Pieces		S
DRL	Length		
54.57	lb/ft	Mass	
Ġ.	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	insp.	Visual	
Pass	OD		Non-E
Pass	ΨT	UΤ	Non-Destructive T
Pass	ASTM E213	TU	Testing
Pass	ASTM E309	ET	
		HydroTest	
37.5° Bevel	Condition	End	

0.01	BSM-0791			
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.20	0.18	0		
0.94	0.93	Mn		
0.014	0.008	P		
0.94 0.014 0.005 0.24	0.004	S		Chemical
0.24	0.25	Si		Chemical Analysis (wt%)
0.03	0.04	ਹ		(wt%)
0.08	0.08	Cu		
0.01	0.01	Mo		
0.04	0.04	Z.		
0.003		<		
0.001	1	77		
0.001	L	Nb		
0.0001	0.0003	В		
0.37	1	(IIW)	CE	
0.38	1	(CSA)	CE	

	BSM-079	Heat		
	BSM-0791 Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	77	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
45,600	42,300	psi	Yield (Rt0.5)	
45,300	44,300	psi	Yield (Rp0.2)	
72,500	73,500	psi	Tensile (Rm)	
0.63	0.58	(Rt0.5/Rm)	Τ/Υ	
44	41	%	Elongation (A)	

Additional Details:

Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the results meet the corresponding requirements. We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.