

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe Product Heat Number:

BSM-0840

Product Size: NPS 20 TRUE80

Production Date: April 16, 2013

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 20 TRUE80 1.031 inchWT HEAT BSM-0840 (PIPE # LENGTH MASS) 208.9Ib/ft NDE SMLS NACE MR0175 2013/04 MADE IN CANADA.

	BSM-0840	Heat		
	10 Heat	Test Type		
	NPS 20 TRUE80 1.031 in.WT	Product Size		Product Detail
	6	Pieces		S
	DRL	Length		
	208.90	lb/ft	Mass	
	Ĝ	μR/hr	Geiger	
	<20	Gauss	Res.Mag.	
	Pass	Insp.	Visual	
	Pass	OD		Non-D
	Pass	WT	TU	Destructive T
	Pass	ASTM E213	TU	[esting
0.00	Pass	M E213 ASTM E309	T3	
	*		HydroTest	
	Plain End	Condition	End	

		В	T	- 12	Π
		BSM-0840			
	Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
	Product	Heat	Analysis		
	0.20	0.19	C		
	0.84	0.88	Mn		
	0.009	0.009	P		
	0.007	0.007	S		Chemical A
	0.24	0.24	Si		Analysis (wt%)
	0.05	0.04	S.		(wt%)
	0.04	0.04	Cu		
	0.01	0.01	Mo		7
200	0.04	0.04	Z.		
	0.002		<		
	0.001	c	Ti		
	0.001		Nb		
	0.0001	0.0003	8		
	0.36	-	(IIW)	CE	
	0.36	ı	(CSA)	Œ	

BS			Γ
BSM-0840	Heat		
Heat	Test Type		
Ferrite & Pearlite	Microstructure		
75	HRBW	Hardness	
Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
41,400	psi	Yield (Rt0.5)	
66,500	psi	Tensile (Rm)	
0.62	(Rt0.5/Rm)	Τ/Υ	
51	%	Elongation (A)	

BSM-0840	Heat	
,	Standard	Test
ı	Sample Details	Impact Test
r	°C	Temp
	٦	
	J	Impact
i	J	Energy
r.	AVG	
1	%	
1	%	% S
ı	%	% Shear
1	AVG	
	mm	
1	mm	Lateral E
	mm	xpansion
	AVG	

Additional Details:

- Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements. ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product.
- This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- ✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.