

Mill Test Certificate

Bri-Steel Manufacturing Inc. 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Tel: 001 (780) 469-6603 Fax: 001 (780) 469-6986 www.brichemsteel.com

May 28, 2013

Seamless Carbon Steel Pipe Product Heat Number: BSM-0934 Product Size: **NPS 14 SCH 120** Production Date:

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product:

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 14 SCH 120 1.094 inchWT HEAT BSM-0934 (PIPE # LENGTH MASS) 150.71b/ft NDE SMLS NACE MR0175 2013/05 MADE IN CANADA.

| BSN | T | | |
|----------------------------|--------------|-----------|-----------------|
| BSM-0934 | Heat | | |
| Heat | Test Type | | |
| NPS 14 SCH 120 1.094 in.WT | Product Size | | Product Details |
| ω | Pieces | | 5 |
| DRL | Length | | |
| 150.70 | lb/ft | Mass | |
| <5 | μR/hr | Geiger | |
| <20 | Gauss | Res.Mag. | |
| Pass | lnsp. | Visual | |
| Pass | OD | | Non-E |
| Pass | WT | TU | Destructive T |
| Pass | ASTM E213 | TU | esting |
| Pass | ASTM E309 | ΕT | |
| * | | HydroTest | |
| Plain End | Condition | End | |

| Г | <u>ш</u> | Τ | - | T |
|----------------------------|-------------------------------------|--------------------|---|-------------------------|
| BSM-0934 | | Heat | | |
| Vacuum Degas; Fully Killed | Blast Furnace; EAF; Ladle Refining; | Steelmaking Method | | |
| Product | Heat | Analysis | | |
| 0.21 | 0.20 | 0 | | |
| 0.93 | 0.92 | Mn | | |
| 0.014 | 0.013 | P | | |
| 0.003 | 0.002 | S | | Chemica |
| 0.35 | 0.34 | Si | | Chemical Analysis (wt%) |
| 0.04 | 0.04 | ڻ | | (wt%) |
| 0.06 | 0.05 | Cı | | |
| 0.01 | 0.03 | M _o | | |
| 0.02 | 0.02 | <u>Z</u> . | | |
| 0.004 | 0.003 | < | | |
| 0.003 | 0.002 | Ti | | |
| 0.001 | 0.001 | Nb | | |
| 0.0001 | 0.0004 | В | | |
| 0.38 | 1 | (WII) | æ | |
| 0.39 | | (CSA) | Œ | |

| BSM | ī | | |
|---------------------------|-----------------|----------------|-----------------------|
| BSM-0934 | Heat | | |
| Heat | Test Type | | |
| Ferrite & Pearlite | Microstructure | | |
| 77 | HRBW | Hardness | |
| Pass | Flattening Test | | Mechar |
| Longitudinal; 38.1mm x WT | 50mm GL | Tension Test | Mechanical Properties |
| 49,200 | psi | Yield (Rt0.5) | |
| 75,000 | psi | Tensile (Rm) | |
| 0.66 | (Rt0.5/Rm) | 1/4 | |
| 54 | % | Elongation (A) | |

| BSI | | |
|----------|----------------|-------------|
| BSM-0934 | неат | |
| 1 | Standard | Test |
| 1 | Sample Details | Impact Test |
| | Oē | Temp |
| 1 | J | |
| | _ | Impact |
| 1 | _ | Energy |
| , | AVG | |
| | % | |
| 1 | % | % Sh |
| | % | Shear |
| | AVG | |
| e | mm | |
| t | mm | Lateral Ex |
| | mm | pansion |
| r | AVG | |

Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1 This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product.
- ✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- ✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

2013 MAY 30

Paul Sowden, T.T. Assistant QA Manager