

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Tel: 001 (780) 469-6603 Fax: 001 (780) 469-6986

www.brichemsteel.com

NPS 14 SCH 120 Production Date: May 28, 2013

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product:

Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0936

Product Size:

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 14 SCH 120 1.094 inchWT HEAT BSM-0936 (PIPE # LENGTH MASS) 150.71b/ft NDE SMLS NACE MR0175

2013/05 MADE IN CANADA.

BSN	T		
BSM-0936	Heat		
Heat	Test Type		
NPS 14 SCH 120 1.094 in.WT	Product Size		Product Details
2	Pieces		5
DRL	Length		
150.70	lb/ft	Mass	
Ġ	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-Dest
Pass	WT	UT	Destructive T
Pass	ASTM E213	TU	esting
Pass	ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

						Chemical A	Analysis (wt%	(wt%)									
																Œ	CE
Heat	Steelmaking Method	Analysis	C	Mn	P	S	Si	C۲	Cn	Mo	Z.	<	∄	Nb	В	(IW)	(CSA)
BSM-0936	Blast Furnace; EAF; Ladle Refining;	Heat	0.21	0.93	0.016	0.002	0.30	0.06	0.06	0.01	0.02	0.005	0.002	0.001	0.0003	ı	t)
	Vacuum Degas; Fully Killed	Product	0.19	0.90	0.014	0.004	0.29	0.07	0.07	0.01	0.02	0.003	0.003	0.001	0.0001	0.36	0.37

_	_		
BSM-0936	Heat		
Heat	Test Type		
Ferrite & Pearlite	Microstructure		
75	HRBW	Hardness	
Pass	Flattening Test		Iviecna
Longitudinal; 38.1mm x WT	50mm GL	Tension Test	iviechanical Properties
46,700	psi	Yield (Rt0.5)	
73,000	psi	Tensile (Rm)	
0.64	(Rt0.5/Rm)	Υ/Τ	
56	%	Elongation (A)	
	Ferrite & Pearlite 75 Pass Longitudinal; 38.1mm x WT 4	Test Type Microstructure HRBW Flattening Test 50mm GL Heat Ferrite & Pearlite 75 Pass Longitudinal; 38.1mm x WT 4	Test Type Microstructure Hardness Tension Test Yield (R Heat Ferrite & Pearlite 75 Flattening Test 50mm GL psi Longitudinal; 38.1mm x WT 46,70

BSM-0936	Heat	
1	Standard	Test
t	Sample Details	Impact Test
1	ΟS	Temp
	_	
ı	_	Impact
	_	Energy
,	AVG	
	%	
	%	% Shea
	%	ear
18	AVG	
	mm	
	mm	Lateral Ex
r	mm	pansion
1	AVG	

Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the $\checkmark~$ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product.
- ✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

RSOMMUN 5102

Paul Sowden, T.T.

Assistant QA Manager