



Mill Test Certificate

Bri-Steel Manufacturing Inc.
 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4
 Tel: 001 (780) 469-6603
 Fax: 001 (780) 469-6986
 www.brichemsteel.com

Product: **Seamless Carbon Steel Pipe**

Product Heat Number: **BSM-0943**

Product Size: **NPS 24 TRUE80**

Product Size: **NPS 24 TRUE80**

Product Size: **NPS 24 TRUE80**

Production Date: **May 28, 2013**

Production Method: **Hot Expansion**

Product Heat Treatment: **As-rolled**

Product Standards: **ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010**

Product Markings: **BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 24 TRUE80 1.219 inchWT HEAT BSM-0943 (PIPE # LENGTH MASS) 296.4lb/ft NDE SMILS NACE MR0175 2013/05 MADE IN CANADA.**

Product Details				Non-Destructive Testing											
Heat	Test Type	Product Size	Pieces	Length	Mass lb/ft	Geiger μ R/hr	Res. Mag. Gauss	Visual Insp.	OD**	UT WT	UT ASTM E213	ET ASTM E309	HydroTest	End Condition	
BSM-0943	Heat	NPS 24 TRUE80 1.219 in.WT	2	DRL	296.40	<5	<20	Pass	Pass	Pass	Pass	Pass	*	Plain End	

Chemical Analysis (wt%)																	
Heat	Steelmaking Method	Analysis	C	Mn	P	S	Si	Cr	Cu	Mo	Ni	V	Ti	Nb	B	CE (IIW)	CE (CSA)
BSM-0943	Blast Furnace: EAF; Ladle Refining; Vacuum Degas: Fully Killed	Heat	0.20	0.90	0.011	0.003	0.27	0.06	0.06	0.02	0.02	0.003	0.001	0.001	0.0003	-	-
	Product	Product	0.20	0.88	0.011	0.004	0.26	0.05	0.07	0.01	0.03	0.002	0.001	0.001	0.0001	0.37	0.37

Mechanical Properties													
Heat	Test Type	Microstructure	Hardness HRBW	Flattening Test	Tension Test 50mm GL	Yield (Rt0.5) psi	Tensile (Rm) psi	Y/T (Rt0.5/Rm)	Elongation (A) %				
BSM-0943	Heat	Ferrite & Pearlite	77	Pass	Longitudinal: 19.1mm x WT	44,400	69,000	0.64	48				
Heat	Test Standard	Impact Test Sample Details	Temp $^{\circ}$ C	J	Impact Energy	% Shear	AVG	mm	Lateral Expansion mm	AVG			
BSM-0943	-	-	-	-	-	-	-	-	-	-			

Additional Details:

- ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements.
- ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service, and NACE MR0103-2010 Section 2.1.
- ✓ No weld repairs have been performed on this product.
- ✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- ✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.
- *Note that this product was hydrotested to 1000 psi for 5 seconds.
- **OD Tolerances as per APISL

Mill Test Certificate approved by:

Paul Sowden
 2013 JUN 03

Paul Sowden, T.T.
 Assistant QA Manager