

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Production Date: May 30, 2013

Production Method: Hot Expansion

Product:

Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0950

Product Size:

NPS 24 TRUE80

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 24 TRUE80 1.219 inchWT HEAT BSM-0950 (PIPE # LENGTH MASS) 296.4lb/ft NDE SMLS NACE MR0175 2013/05 MADE IN CANADA.

<u></u>	Т		Т
BSM-0950	Heat		
Heat	Test Type		
NPS 24 TRUE80 1.219 in.WT	Product Size		Product Details
4	Pieces		J.
DRL	Length		
296.40	lb/ft	Mass	
S	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD**		Non-Destruc
Pass	WT	TU	Destructive .
Pass	ASTM E213	UT	esting
Pass	ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

						Chemical	Chemical Analysis (wt%)	(wt%)									
																GE	CE
Heat	Steelmaking Method	Analysis	C	Mn	P	s	Si	Cr	Cu	Mo	Z.	<	Ⅎ	Вb	Φ	(IW)	(CSA)
BSM-0950	Blast Furnace; EAF; Ladle Refining;	Heat	0.20	0.85	0.016	0.003	0.33	0.04	0.07	0.02	0.03	0.003	0.002	0.001	0.0003	1	1
	Vacuum Degas; Fully Killed	Product	0.22	0.90	0.017	0.003	0.28	0.05	0.05	0.01	0.03	0.005	0.002	0.001	0.0001	0.39	0.40

				Mechar	Mechanical Properties				
			Hardness		Tension Test	Yield (Rt0.5)	Tensile (Rm)	Υ/Τ	Elongation (A)
Heat	Test Type	Microstructure	HRBW	Flattening Test	50mm GL	psi.	psi	(Rt0.5/Rm)	%
BSM-0950	Heat	Ferrite & Pearlite	73	Pass	Longitudinal; 19.1mm x WT	42,700	69,500	0.61	50

BSM-	Heat	
-0950	tat	
,	Standard	Test
1	Sample Details	Impact Test
	Je C	Temp
E:	_	
c	_	Impact
r	_	Energy
ı	AVG	
1	%	
,	%	% Shea
1	%	Shear
1	AVG	
1	mm	
1	mm	Lateral E
r	mm	xpansion
,	AVG	

Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product.
- This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- $\checkmark~$ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.
- *Note that this product was hydrotested to 1000 psi for 5 seconds.
- **OD Tolerances asper API

Mill Test Certificate approved by:

Paul Sowden, T.T. 20/30 W 07 South

Assistant QA Manager