

## Mill Test Certificate

**Bri-Steel Manufacturing Inc.** 

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe Product Heat Number: BSM-0973

Product Size: NPS 24 TRUE80 Production Date:

June 6, 2013

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 24 TRUE80 1.219 inchWT HEAT BSM-0973 (PIPE # LENGTH MASS) 296.4lb/ft NDE SMLS NACE MR0175 2013/06 MADE IN CANADA.

BSM-0973	Heat		
Heat	Test Type		
NPS 24 TRUE80 1.219 in.WT	Product Size		Product Detail
2	Pieces		S
DRL	Length		
296.40	lb/ft	Mass	
<b>S</b>	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-I
Pass	WT	TU	Destructive 1
Pass	ASTM E213	TU	esting
Pass	ASTM E309	旦	
*		HydroTest	
Plain End	Condition	End	

_	_	_		_
	BSM-0973	Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.20	0.22	0		
0.88	0.90	Mn		
0.016 0.007	0.014 0.004	P		
0.007	0.004	S		Chemical Analysis (wt%)
0.32	0.32	Si		Analysis
0.05	0.05	Ç		(wt%)
0.06	0.06	C		
0.01	0.00	Mo		
0.03	0.03	Ζ.		
0.005	0.004	<		
0.003	0.003	Ti		13.00
0.001	0.001	Nb		
0.0001	0.0003	В		
0.37		(WII)	æ	
0.38		(CSA)	Œ	

				Media	Mechanical Properties				
		2 200	Hardness		Tension Test	Yield (Rt0.5)	Tensile (Rm)	٧/٢	Elongation (A)
Heat	Test Type	Microstructure	HRBW	Flattening Test	50mm GL	psi	psi.	(Rt0.5/Rm)	%
BSM-0973	Heat	Ferrite & Pearlite	79	Pass	Longitudinal; 19.1mm x WT	44,800	71,000	0.63	45

	BSM-0973	Heat	
	t	Standard	Test
	1	Sample Details	Impact Test
		O <sub>e</sub>	Temp
	1	_	
	i	_	Impact
200		_	Energy
	•	AVG	
	t	%	
	1	%	% Sh
	ı	%	ear
		AVG	i i
	1	mm	
	1	mm	Lateral Ex
	1	 mm	(pansion
	1	 AVG	

## Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. √ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product.
- This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- ✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

\*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. 2013 June 12

Manager of Quality and R&D