

Mill Test Certificate

Bri-Steel Manufacturing Inc.

Tel: 001 (780) 469-6603

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0979

Product Size:

NPS 24 TRUE80

Production Date: June 6, 2013

Production Method: Hot Expansion Product Heat Treatment:

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

As-rolled

Product Markings: BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 24 TRUE80 1.219 inchWT HEAT BSM-0979 (PIPE # LENGTH MASS) 296.4lb/ft NDE SMLS NACE MR0175 2013/06 MADE IN CANADA.

| Plain En | * | Pass | Pass | Pass | Pass | Pass | <20 | S | 296.40 | DRL | р- | NPS 24 TRUE80 1.219 in.WT | Heat | BSM-0979 |
|----------|-----------|-----------|-----------|--------------|-------|--------|----------|----------|--------|--------|--------|---------------------------|-----------|----------|
| Conditio | | ASTM E309 | ASTM E213 | WT | OD | Insp. | Gauss | μR/hr | lb/ft | Length | Pieces | Product Size | Test Type | Heat |
| End | HydroTest | ET | TU | TU | | Visual | Res.Mag. | Geiger | Mass | | | | | |
| | | | esting | estructive T | Non-E | | | | | | S | Product Detail | | |

| | | _ | | _ |
|----------------------------|-------------------------------------|--------------------|---|-------------------------|
| | BSM-0979 | Heat | | |
| Vacuum Degas; Fully Killed | Blast Furnace; EAF; Ladle Refining; | Steelmaking Method | | |
| Product | Heat | Analysis | | |
| 0.21 | 0.22 | С | | |
| 0.90 | 0.90 | Mn | | |
| 0.018 0.003 | 0.011 | P | | |
| 0.003 | 0.004 | S | | Chemical Analysis (wt%) |
| 0.28 | 0.30 | Si | | Analysis |
| 0.05 | 0.04 | C. | | (wt%) |
| 0.07 | 0.10 | Cn | | |
| 0.01 | 0.01 | Mo | | |
| 0.03 | 0.04 | Z. | | |
| 0.006 | 0.004 | < | | |
| 0.003 | 0.002 | T | | |
| 0.001 | 0.001 | Nb | | |
| 0.0002 | 0.0004 | В | | |
| 0.38 | t | (IIW) | Œ | |
| 0.39 | , | (CSA) | æ | |

| Г | Т | | Т |
|---------------------------|-----------------|----------------|------------------|
| BSM-0979 | Heat | | |
| Heat | Test Type | | |
| Ferrite & Pearlite | Microstructure | | |
| 79 | HRBW | Hardness | |
| Pass | Flattening Test | | Mechanical |
| Longitudinal; 19.1mm x WT | 50mm GL | Tension Test | lical Properties |
| 49,900 | psi | Yield (Rt0.5) | |
| 73,500 | psi | Tensile (Rm) | |
| 0.68 | (Rt0.5/Rm) | Τ/Α | |
| 47 | % | Elongation (A) | |
| _ | | _ | |

| | В | | | |
|----------|----------------|----------------|-------------|--|
| BSM-0979 | | Heat | | |
| | | Standard | Test | |
| 1 | | Sample Details | Impact Test | |
| Ċ | | Οē | Temp | |
| , | | _ | | |
| | | _ | Impact | |
| | | <u>_</u> | Energy | |
| 1 | | AVG | | |
| , | | % | | |
| | | % | % Shea | |
| 1 | | % | hear | |
| - | | AVG | | |
| | - | mm | | |
| - | | mm | ateral Ex | |
| • | 3370 C 238 550 | m m | pansion | |
| 1 | | AVG | | |

Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- ✓ No weld repairs have been performed on this product.
- This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- √ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.
- *Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

2013 June (2

Manager of Quality and R&D Kenton Dechant, P.Eng.