

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Product Size: **NPS 20 SCH 60** Production Date: June 14, 2013

Production Method: **Hot Expansion** Product Heat Treatment: As-rolled

Product:

Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0992

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 20 SCH 60 0.812 inchWT HEAT BSM-0992 (PIPE # LENGTH MASS) 166.4lb/ft NDE SMLS NACE MR0175 2013/06 MADE IN CANADA.

BSM-0992	Heat		
92 Heat	Test Type		
at	Гуре		
NPS 20 SCH 60 0.812 in.WT	Product Size		Product Details
5	Pieces		
DRL	Length		
166.40	lb/ft	Mass	
S	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-I
Pass	WT	TU	Destructive 1
Pass	ASTM E213	TU	esting
Pass	ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

						Chemica	Chemical Analysis (wt%	(wt%)									
																CE	Œ
Heat	Steelmaking Method	Analysis	C	Mn	P	S	Si	Cr	Cu	Mo	Z.	<	∄	Вb	В	(W)	(CSA)
BSM-0992	Blast Furnace; EAF; Ladle Refining;	Heat	0.19	0.88	0.012	0.008	0.27	0.05	0.06	0.01	0.04		1		0.0003	ı	ı
	Vacuum Degas; Fully Killed	Product	0.20	0.88	0.013	0.009	0.26	0.06	0.07	0.01	0.04	0.004	0.001	0.001	0.0002	0.37	0.38

BSM-0992	Heat		
Heat	Test Type		
Ferrite & Pearlite	Microstructure		
77	HRBW	Hardness	
Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
43,600	psi	Yield (Rt0.5)	
73,500	psi	Tensile (Rm)	
0.59	(Rt0.5/Rm)	Τ/Υ	
48	%	Elongation (A)	

BSM-0992	Heat		
ı	Standard	Test	
•	Sample Details	Impact Test	
1	Os.	Temp	
ı	_		
1	_	Impact	
i	J	Energy	
•	AVG		
i	%		
	%	% Shea	
	%	near	
i.	AVG		
r.	mm		
·	mm	Lateral Ex	
,	mm	Expansion	
	AVG		

Additional Details:

Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

results meet the corresponding requirements.

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

*Note that this product was hydrotested to 1000 psi for 5 seconds. $\checkmark~$ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Paul Sowden, T.T.

Assistant QA Manager