

## Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Production Date: June 18, 2013

Production Method: Hot Expansion

Product:

Seamless Carbon Steel Pipe

Product Heat Number:

BSM-1004

Product Size:

NPS 36 STD

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: 500 PSI SMLS NACE MR0175 2013/06 MADE IN CANADA. BRI-STEEL MFG <API> 5L-0898 API 5L GR B PSL1 ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 36 STD 0.375 inchWT HEAT BSM-1004 (PIPE # LENGTH MASS) 142.71b/ft NDE

	_	Т		Г
	BSM-1004	Heat		
	Heat	Test Type		
	NPS 36 STD 0.375 in.WT	Product Size		Product Details
	1	Pieces		S
0	DRL	Length		
	142.70	lb/ft	Mass	
100000000000000000000000000000000000000	<b>\$</b> 5	μR/hr	Geiger	
000	<20	Gauss	Res.Mag.	
	Pass	Insp.	Visual	
	Pass	OD		Non-Destructiv
	Pass	WT	TU	Destructive T
	Pass	ASTM E213	TU	e Testing
	Pass	M E213 ASTM E309 500 psi/5s	ΕT	
	Pass	500 psi/5s	HydroTest	
	32.5° Bevel	Condition	End	

						Chemical	Chemical Analysis (wt%	(wt%)									
4																Œ	CE
Heat	Steelmaking Method	Analysis	C	Mn	P	S	Si	Cr	Cu	Mo	Z.	<	=	В	В	(E)	(CSA)
RSM-1004	Blast Furnace; EAF; Ladle Refining;	Heat	0.20	0.87	0.009	0.014	0.21	0.03	0.06	0.01	0.04	ı		1	0.0001	ı	£
	Vacuum Degas; Fully Killed	Product	0.22	0.88	0.011	0.019	0.22	0.03	0.08	0.02	0.04	0.003	0.001	0.001	0.0002	0.38	0.39

[[	Т		Τ
3SM-1004	Heat		
Heat	Test Type		
Ferrite & Pearlite	Microstructure		
73	HRBW	Hardness	
Pass	Flattening Test		Mechan
Longitudinal; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
42,900	psi	Yield (Rt0.5)	
69,000	psi	Tensile (Rm)	
0.62	(Rt0.5/Rm)	1/4	
44	%	Elongation (A)	
	Heat Ferrite & Pearlite 73 Pass Longitudinal; 38.1mm x WT 42,900 69,000	Test Type Microstructure HRBW Flattening Test 50mm GL psi psi (Rt0.5/Rm)  Heat Ferrite & Pearlite 73 Pass Longitudinal; 38.1mm x WT 42,900 69,000 0.62	Test TypeMicrostructureHardnessTension TestYield (Rt0.5)Tensile (Rm)Y/TElongaHeatFerrite & Pearlite73PassLongitudinal; 38.1mm x WT42,90069,0000.624

	BSM-100	Heat		
	004	S	_	
	,	tandard	Test	
		Sample Details	Impact Test	
	,	2°C	Temp	
	,	_		
	,	J	Impact	
		J	Energy	
S. C.	ı	AVG		
	r	%		
	t	%	% Shea	
	ı	%	near	
		AVG		
		mm		
	r	mm	Lateral E	
	r	mm	xpansion	
	1	AVG		

## Additional Details:

- and that the results meet the corresponding requirements. Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements,  $\checkmark~$  We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product.
- ✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- $\checkmark~$  This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Paul Sowden, T.T.

Assistant QA Manager