



Mill Test Certificate

Bri-Steel Manufacturing Inc.
 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4
 Tel: 001 (780) 469-6603
 Fax: 001 (780) 469-6986
 www.brichemsteel.com

Product: **Seamless Carbon Steel Pipe** Product Heat Number: **BSM-1006** Product Size: **NPS 18 STD** Production Date: **June 24, 2013**

Production Method: **Hot Expansion** Product Heat Treatment: **As-rolled**

Product Standards: **ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C, NACE MR0175-2009, MR0103-2010**

Product Markings: **BRI-STEEL MFG <API> 5L-0898 API 5L GR B PSL1 ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 18 STD 0.375 inchWT HEAT BSM-1006 (PIPE # LENGTH MASS) 70.59lb/ft**
NDE 1000 PSI SMILS NACE MR0175 2013/06 MADE IN CANADA.

Product Details				Non-Destructive Testing											
Heat	Test Type	Product Size	Pieces	Length	Mass lb/ft	Geiger μ R/hr	Res. Mag. Gauss	Visual Insp.	OD	WT	UT	UT	ET	HydroTest	End Condition
BSM-1006	Heat	NPS 18 STD 0.375 in. WT	3	DRL	70.59	<5	<20	Pass	Pass	Pass	Pass	Pass	Pass	Pass	32.5° Bevel

Chemical Analysis (wt%)																	
Heat	Steelmaking Method	Analysis	C	Mn	P	S	Si	Cr	Cu	Mo	Ni	V	Ti	Nb	B	CE (IIW)	CE (CSA)
BSM-1006	Blast Furnace: EAF; Ladle Refining; Vacuum Degas: Fully Killed	Heat	0.20	0.90	0.008	0.006	0.25	0.03	0.11	0.01	0.05	-	-	-	0.0004	-	-
		Product	0.22	0.92	0.007	0.010	0.26	0.06	0.12	0.01	0.04	0.003	0.001	0.001	0.0004	0.40	0.41

Mechanical Properties									
Heat	Test Type	Microstructure	Hardness HRBW	Flattening Test	Tension Test 50mm GL	Yield (Rt0.5) psi	Tensile (Rm) psi	Y/T (Rt0.5/Rm)	Elongation (A) %
BSM-1006	Heat	Ferrite & Pearlite	77	Pass	Longitudinal; 38.1mm x WT	45,700	73,000	0.63	40

Heat	Test Standard	Impact Test Sample Details	Temp $^{\circ}$ C	Impact Energy			Lateral Expansion					
				J	J	AVG	%	mm	mm	AVG		
BSM-1006	-	-	-	-	-	-	-	-	-	-	-	-

- Additional Details:
- ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with API 5L-44th Ed, ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements.
 - ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service, and NACE MR0103-2010 Section 2.1.
 - ✓ No weld repairs have been performed on this product.
 - ✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
 - ✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Paul Sowden

2013 JUN 27

Paul Sowden, T.T.
 Assistant QA Manager