

## Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.brichemsteel.com

NPS 24 STD Production Date: July 4, 2013

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product:

Seamless Carbon Steel Pipe

Product Heat Number:

BSM-1046

Product Size:

Product Standards: ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: NDE 750 PSI SMLS NACE MR0175 2013/07 MADE IN CANADA. BRI-STEEL MFG <API> 5L-0898 API 5L GR B PSL1 ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 24 STD 0.375 inchWT HEAT BSM-1046 (PIPE # LENGTH MASS) 94.62lb/ft

	BSM-1046	Heat		T
	046			
	Heat	Test Type		
	NPS 24 STD 0.375 in.WT	Product Size		Product Detail
	2	Pieces		S
	DRL	Length		
	94.62	lb/ft	Mass	
	6	μR/hr	Geiger	
	<20	Gauss	Res.Mag.	
	Pass	Insp.	Visual	
	Pass	OD		Non-D
	Pass	TW	TU	Destructive T
	Pass	ASTM E213	TU	esting
	Pass	ASTM E309	ET	
┕	Pass	9 750 psi/5s	HydroTest	
	32.5° Bevel	Condition	End	

						Chemical	Chemical Analysis (wt%	(wt%)									
Heat	Steelmaking Method	Analysis	n	5	D	Λ	<u>ς</u>	,	3	5	<u>.</u>	<	;	5	9	CE	CE
	0	· · · · · · · · · · · · ·	,		-	,	٢	2	ç	Į,	IN.	<	=	No	0	(1100)	(CSA)
BSM-1046	Blast Furnace; EAF; Ladle Refining;	Heat	0.21	0.96	0.010	0.010	0.22	0.04	0.06	0.02	0.03	ı		ı	0.0003		e.
1	Vacuum Degas; Fully Killed	Product	0.23	0.97	0.011	0.011	0.22	0.04	0.06	0.02	0.03	0.004	0.001	0.001	0.0002	0.41	0.42
	The second secon										300000000000000000000000000000000000000		COCCOSCICCION CO.	202000000000000000000000000000000000000	_	The second second	

BSM	Į		
BSM-1046	Heat		
Heat	17		
Ferrite & Pearlite	Microstructure		
79	HRBW	Hardness	
Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
52,500	psi	Yield (Rt0.5)	
73,000	psi	Tensile (Rm)	
0.72	(Rt0.5/Rm)	1/4	
40	%	Elongation (A)	

BSM-1046	Heat	
1	Standard	Test
1	Sample Details	Impact Test
	C	Temp
	_	
1	J	Impact
1	٦	Energy
	AVG	
ı.	%	
1	· %	% Shear
	%	near
t	AVG	
ı	mm	
E	mm	Lateral E
Ü	mm	xpansion
	AVG	

Additional Details:

and that the results meet the corresponding requirements. Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. √ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

 $\checkmark~$  This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Paul Sowden, T.T.

Assistant QA Manager