

## Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Production Date: April 24, 2013

Product Heat Number: BSM-1066

Product Size:

NPS 16 SCH 100

Product:

Seamless Carbon Steel Pipe

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 16 SCH 100 1.031 inchWT HEAT BSM-1066 (PIPE # LENGTH MASS) 164.81b/ft NDE SMLS NACE MR0175 2013/04 MADE IN CANADA.

BSM-1066	Heat		
Heat	lest Type		
NPS 16 SCH 100 1.031 in.WT	Product Size		Product Detail
2	Pieces		S
DRL	Length		
164.80	lb/ft	Mass	
G	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	lnsp.	Visual	
Pass	OD		Non-I
Pass	WT	TU	Destructive T
Pass	ASTM E213	TU	esting
Pass	ASTM E309	ET	
-		HydroTest	
Plain End	Condition	End	

						Chemical	Chemical Analysis (wt%	(wt%)									
L 02+	Ctoolmaking Mathod	2	)	:	,	n	?	)	)			8				CE	CE
Heat	Steelmaking Method	Analysis	C	Μ	Р	S	Si	ç.	Cu	Mo	Z.	<	=!	N <sub>P</sub>	Ф	(EX)	(CSA)
BSM-1066	Blast Furnace; EAF; Ladle Refining;	Heat	0.22	0.90	0.012	0.002	0.32	0.05	0.06	0.01	0.02	0.002	0.002	0.001	0.0003	ı	ı
	Vacuum Degas; Fully Killed	Product	0.21	0.88	0.021	0.005	0.30	0.06	0.06	0.01	0.03	0.005	0.001	0.001	0.0002	0.38	0.39

BSM-1066   Heat   Ferrite & Pearlite   78   Pass   Longitudinal; 19.1mm ;			Wechanical Properties
78		Hardness	
	lattening Test		Iviechan
Longitudinal; 19.1mm x WT	50mm GL	Tension Test	ical Properties
50,000	psi	Yield (Rt0.5)	
74,500	psi	Tensile (Rm)	
0.67	(Rt0.5/Rm)	Т/А	
42	%	Elongation (A)	

## Additional Details:

BSM-1066

Standard

Sample Details Impact Test

Temp 9C

Impact Energy

AVG

%

%

AVG

mm

mm

mm

AVG

Lateral Expansion

% Shear %

Test

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

 $\checkmark$  This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

013 146 17

Assistant QA Manager Paul Sowden, T.T.