

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-1118

NPS 18 SCH 120

July 30, 2013

Production Method: **Hot Expansion**

Product Heat Treatment:

As-rolled

Product Size:

Production Date:

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 18 SCH 120 1.375 inchWT HEAT BSM-1118 (PIPE # LENGTH MASS) 244.1lb/ft NDE SMLS NACE MR0175 2013/07 MADE IN CANADA.

BSM.	Heat		
BSM-1118	+		
Heat	Test Type		
NPS 18 SCH 120 1.375 in.WT	Product Size		Product Detail
5	Pieces		S
DRL	Length		
244.10	lb/ft	Mass	
Ġ	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-I
Pass	WT	TU	Destructive 1
Pass	ASTM E213	UT	esting
Pass	ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

0	0.40	0.0002	0.001	0.002	0.005	0.03	0.02	0.08	0.08	0.32	0.004	0.014 0.004 0.32	0.93	0.22	Product	Vacuum Degas; Fully Killed	
	\vdash	0.0004	0.001	0.002	0.004	0.03	0.02	0.08	0.07	0.30	0.003	0.014	0.91	0.21	Heat	Blast Furnace; EAF; Ladle Refining;	BSM-1118
(IIW		В	Nb	⊐	<	<u>Z</u>	Mo	Cu	Ç	Si	S	7	Ŋ,	C	Analysis	Steelmaking Method	Heat
Œ										3						ATTENNEY 20 - 20 ATT - PRODUCT SOUTH - DA	
	1								(wt%)	Chemical Analysis (wt%)	Chemica						

Vield (Rt0.5) Tensile (Rm) Y/T Elongation (A) psi psi (Rt0.5/Rm) % 49,300 76,000 0.65 48
1.5) Tensile (Rm) Y/T Elongs psi (Rt0.5/Rm) 76,000 0.65
n Test Yield (Rt0.5) Tensile (Rm) Y/T Elongs n GL psi psi (Rt0.5/Rm) 19.1mm x WT 49,300 76,000 0.65
1.5) Tensile (Rm) Y/T Elongs psi (Rt0.5/Rm) 76,000 0.65
e (Rm) Y/T Elongs ssi (Rt0.5/Rm) 000 0.65
Rm) Elong:
Elongation (A) %
1 1

	_	т—	
	BSM-1118	Heat	
		Standard	Test
	t	Sample Details	Impact Test
	1	°C	Temp
	,	١	
		J	Impact
	t	_	Energy
	,	AVG	
	3	%	
	,	%	% Shea
	1	%	ear
		AVG	
		mm	
	1	mm	Lateral Ex
	,	mm	(pansion
	•	AVG	

Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the $\checkmark~$ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1 ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product.
- This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- ✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

2013 Aug

Kenton Dechant, P.Eng

Manager of Quality and R&D