

## Mill Test Certificate

**Bri-Steel Manufacturing Inc.** 

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-1131

NPS 18 TRUE80

Production Method: Hot Expansion

Product Size:

Production Date: August 6, 2013

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

**Product Markings:** BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 18 TRUE80 0.94 inchWT HEAT BSM-1131 (PIPE # LENGTH MASS) 170.8Ib/ft NDE SMLS NACE MR0175 2013/08 MADE IN CANADA.

	_		_
BSM-1131	Heat		
Heat	Test Type		
NPS 18 TRUE80 0.94 in.WT	Product Size		Product Detail
2	Pieces		ls
DRL	Length		
170.80	lb/ft	Mass	
<b>\$</b>	µR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-E
Pass	WT	TU	estructive :
Pass	ASTM E213	TU	Testing
Pass	ASTM E309	ET	000000000000000000000000000000000000000
*		HydroTest	
Plain End	Condition	End	

	BSM-1131	Heat		
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.21	0.21	C		
0.91	0.91	Mn		
0.015	0.015	P		
0.003	0.003	S		Chemical
0.30	0.32	Si		ical Analysis (wt%)
0.05	0.04	Cr		(wt%)
0.07	0.06	Cu		
0.01	0.01	Mo		
0.03	0.02	Z.		
0.004	0.003	<		
0.002	0.002	Ħ.		
0.001	0.001	Nb		
0.0001	0.0002	В		
85.0	1	(WII)	Œ	
0.39		(CSA)	Œ	

BSM-1131 Heat	Heat Test Type		
Ferrite & Pearlite	Microstructure		
77	HRBW	Hardness	
Pass	Flattening Test		Mechar
Longitudinal; 19.1mm x WT	50mm GL	Tension Test	Mechanical Properties
49,200	psi	Yield (Rt0.5)	
68,500	psi	Tensile (Rm)	
0.72	(Rt0.5/Rm)	Τ/Υ	
48	%	Elongation (A)	

Impact Energy J AVG %	act Energy %	J AVG	act Energy %	act Energy % Shear / % % % / % / % / % / / / / % / % / / / / / / / / / / / / / / / / / / / /	J         AVG         %         %         AVG	J AVG % % AVG mm
NG	WG % %	WG % %	%Shear	% Shear	VG         %         %         AVG         mm	WG % % AVG mm mm
NG	WG % %	WG % %	%Shear	% Shear	VG         %         %         AVG         mm	WG % % AVG mm mm
- %	- % %	- % %	% Shear	% Shear % AVG	%Shear La	% Shear Lateral Expa
	- % Sh	% Shear %	- %	% AVG	% AVG mm	% AVG mm mm

Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- ✓ No weld repairs have been performed on this product.
- This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- √ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.
- \*Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng. 2013 Aug 8