

## Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 **Bri-Steel Manufacturing Inc.** 

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Production Date:

August 13, 2013

Production Method:

Product:

Seamless Carbon Steel Pipe

Product Heat Number: BSM-1160

Product Size:

NPS 14 STD

**Hot Expansion** Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, API 5L-44th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: BRI-STEEL MFG <API> 5L-0898 API 5L GR B PSL1 ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 14 STD 0.375 inchWT HEAT BSM-1160 (PIPE # LENGTH MASS) 54.571b/ft NDE 1140 PSI SMLS NACE MR0175 2013/08 MADE IN CANADA.

	_	_	1
BSM-1160	Heat		
Heat	Test Type		
NPS 14 STD 0.375 in.WT	Product Size		Product Details
1	Pieces		S
DRL	Length		
54.57	lb/ft	Mass	
Ġ	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-I
Pass	WT	TU	Destructive T
Pass	ASTM E213	디	esting
Pass	ASTM E309	ET	
Pass	1140 psi/5s	HydroTest	
32.5° Bevel	Condition	End	
	NPS 14 STD 0.375 in.WT 1 DRL 54.57 <5 <20 Pass Pass Pass Pass Pass Pass	Test TypeProduct SizePiecesLengthlb/ftμR/hrGaussInsp.ODWTASTM E213ASTM E309140 psi/5sHeatNPS 14 STD 0.375 in.WT1DRL54.57<5	Test TypeProduct SizePiecesLengthlb/ftμR/hrGaussInsp.ODWTASTM E213ASTM E2091140 psi/5sHeatNPS 14 STD 0.375 in.WT1DRL54.57<5

-	BSN	Heat		
	BSM-1160		8	
Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
Product	Heat	Analysis		
0.22	0.20	0		
0.91	0.89	Mn		
0.013	0.013	P		
0.22 0.91 0.013 0.003 0.24 0.04	0.013 0.004 0.24	S		Chemical
0.24	0.24	Si		Chemical Analysis (wt%)
0.04	0.04	Cr		(wt%)
0.06	0.05	Cn		
0.01	0.01	Mo		
0.03	0.03	Z.		
0.003		<		
0.002	-	ī		
0.001	t	Nb		
0.0002	0.0002	В		
0.39	-	(IW)	Œ	
0.40	-	(CSA)	CE	

Mechanical Properties
Hardness Tension Test Yield (Rt0.5) Tensile (Rm) Y/T Elongat
Heat Test Type Microstructure HRBW Flattening Test 50mm GL psi psi (Rt0.5/Rm) %
BSM-1160 Heat Ferrite & Pearlite 73 Pass Longitudinal; 38.1mm x WT 45,500 72,000 0.63 4;

	BSM-1160	Heat		
	1	Standard	Test	
	ı	Sample Details	Impact Test	
	ĭ	)s	Temp	
		_		
	1	J	Impact	
	-	J	Energy	
	-	AVG		
		%	% Shear	
	•	%		
200		%		
		AVG		
	1	mm		
	1	mm	Lateral Ex	
200000		mm	xpansion	
-	1	AVG		

## Additional Details:

and that the results meet the corresponding requirements. Inc. in accordance with API 5L-44th Ed., ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. √ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

2013 AUG 23 Obserden

Paul Sowden, T.T.

Assistant QA Manager