

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 **Bri-Steel Manufacturing Inc.**

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986 www.brichemsteel.com

BSM-1167 Product Size:

Product Heat Number:

NPS 14 XS

Production Date: August 21, 2013

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product:

Seamless Carbon Steel Pipe

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 14 XS 0.5 inchWT HEAT BSM-1167 (PIPE # LENGTH MASS) 72.091b/ft NDE SMLS NACE MR0175 2013/08 MADE IN CANADA.

	В	Ī		Г
	BSM-1167	Heat		
1000	Heat	Test Type		
	NPS 14 XS 0.5 in.WT	Product Size		Product Detail
	4	Pieces		S
	DRL	Length		
	72.09	lb/ft	Mass	
	_ራ	μR/hr	Geiger	
	<20	Gauss	Res.Mag.	60
	Pass	Insp.	Visual	
	Pass	OD		Non-I
	Pass	WT	TU	Destructive 1
	Pass	ASTM E213	TU	esting
	Pass	ASTM E309	ET	
			HydroTest	
	32.5° Bevel	Condition	End	

						Chemica	Chemical Analysis (wt%)	(wt%)									
																CE	E E
Heat	Steelmaking Method	Analysis	С	Mn	Р	S	Si	Ç	5	Mo	<u>z</u> .	<	#	Nb	В	(IW)	(CSA)
BSM-1167	Blast Furnace; EAF; Ladle Refining;	Heat	0.19	0.86	0.010	0.005	0.21	0.04	0.06	0.01	0.04	ť	E	ť	0.0003	e.	1
	Vacuum Degas; Fully Killed	Product	0.20	0.87	0.011 0.006	0.006	0.25	0.04	0.08	0.01	0.04	0.003	0.002	0.001	2000.0	0.36	0.37

BSM-1167	Heat		
Heat	Test Type		
Ferrite & Pearlite	Microstructure		
76	HRBW	Hardness	
Pass	Flattening Test		Mechai
Longitudinal; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
45,300	psi	Yield (Rt0.5)	
74,000	psi	Tensile (Rm)	
0.61	(Rt0.5/Rm)	Τ/Υ	
 46	%	Elongation (A)	

Additional Details:

BSM-1167

Standard

Sample Details Impact Test

Temp °C

Impact Energy

AVG

%

%

AVG

mm

mm

mm

AVG

Lateral Expansion

% Shear %

Test

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012, and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

 $\checkmark~$ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

2013 AUGUV

Souden

Paul Sowden, T.T.

Assistant QA Manager