

Mill Test Certificate

Bri-Steel Manufacturing Inc. 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986 www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-1222

Product Size: 20 XS

Production Date:

Production Method: **Hot Expansion**

> **Product Heat Treatment:** As-rolled

ASME B36.10-2004, API 5L-45th Ed. Grade B PSL1, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010

Certificate No.: MTR- 000441 Sep 09, 2013

Product Standards:

Product Markings | API> 51-0898 API SPEC 5L NPS 20 XS 0.500 INCHWT GR B PSL1 SMLS 2013/09 NDE 1200PSI

BSM-1222		Heat	
. Heat		Test Type	
NPS 20 XS 0.500in. WT		Product Size	Product: Details
2		Pieces	
DRL		Length	
104.1	lb/ft	Mass	
<5	μR/hr	Geiger	2000
< 20	Gauss	Res. Mag.	
Pass	Insp.	Visual	
Pass		OD	N
Pass	WT	TU	on-Destruc
Pass	ASTM E213 ASTM	TU	Non-Destructive Testing
Pass		ET	
Pass	1200 PSI/ 5 s Condition	HydroTest	
32.5° Bevel	s Condition	End	

Heat				BSM-1222	Heat	
Test Type			Degas, raily silied	Blast Furnace; EAF; Ladle Refining; Vacuum	Steelmak	
Microstructure				dle Refining; Vacuum	Steelmaking Method	
Har			Product 0.19 0.90 0.013 0.010 0.23	Heat	Test Type	
Hardness			0.19	0.18	С	
Flatten			0.90	0.91	Mn	
Flattening Test			0.013	0.91 0.010 0.010 0.22	Р	
Tension Test	Mechanical Properties	Mechanical Properties	0.010	0.010	S	Chemical Analysis (wt%)
				0.22	Si	
			0.03	0.03	Cr	
			0.08	0.08	Cu	
Yiel			0.01	0.04	Mo	
Yield (Rt0.5)			0.04	0.04	Ni	
Tensile (Rm)			0.002	0.001	٧	
e (Rm)			0.001	0.001	Ti	
T/γ		2000	0.001	0.001	Nb	
			0.001 0.0002 0.36	0.0005	В	
Elongation (A)			0.36	-	CE(IIW) CE(CSA)	
on (A)			0.36	1	CE(CSA)	

_				_	_		_		
RSM-1222		Heat		BSM-1222		Heat			
Standard		Test		Heat		Test Type			
0.0	rd.			Ferrite & Pearlite		Microstructure			
	Samp	lmp: Samp		Ė		(D			
-	Sample Details	Impact Test		75 HRBW		Hardness			
	Temp °C			Pass		Flattening Test			
	J								
	J	Impact Energy	Impact Energy		Longitudinal; 38.1 mm x \	5	Tei		
	J				al; 38.1 n	50mm GL	Tension Test		
t	AVG		0.000	າm x WT		-			
	%	% Shear				Yie			
	%		% Sh	% Sh		43,900	psi	Yield (Rt0.5)	
Iŝ	%		3000	71		Tensi			
	AVG			71,000	osi	Tensile (Rm)			
	mm	Lateral Expansion		0.62	(Rt0.5/Rm)	٧/٢			
	mm			į	Rm)				
	mm		xpansion		48	%	Elongation (A)		
	AVG			}		ion (A)			

Additional Details:

- ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with API 5L-45th Ed., ASTM/ASME A/SA106-2011 Grade B/C A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements.
- \checkmark This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2010 Section 2.1
- ✓ No weld repairs have been performed on this product.
- \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

of som den 2013 SEP 18

Paul Sowden, T.T.

Assistant QA Manager