

## Mill Test Certificate

Bri-Steel Manufacturing Inc. 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Seamless Carbon Steel Pipe Product Heat Number: BSM-1298 Product Size: 18 TRUE 80

Product:

Production Date: Oct 08, 2013

Product Standards: Production Method: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010 **Hot Expansion** Product Heat Treatment: As-rolled Certificate No.: MTR- 000505

**Product Markings** NPS 18 TRUE 80 0.940 INCHWT SMLS 2013/10 NDE

|          |           | Product: Details           |        |        |       |        |           |        | N    | Non-Destructive Testin | ive Testing |      |           |           |
|----------|-----------|----------------------------|--------|--------|-------|--------|-----------|--------|------|------------------------|-------------|------|-----------|-----------|
| Heat     | Test Type | Product Size               | Pieces | Length | Mass  | Geiger | Res. Mag. | Visual | OD   | TU                     | TU          | ET   | HydroTest | End       |
|          |           |                            |        |        | lb/ft | μR/hr  | Gauss     | insp.  |      | WT                     | ASTM E213   | ASTM |           | Condition |
| BSM-1298 | Heat      | NPS 18 TRUE 80 0.940in. WT | ω      | DRL    | 170.8 | ç,     | <10       | Pass   | Pass | Pass                   | Pass        | Pass | *         | Plain End |

|                  | BSM-1298 | Heat               |                         |
|------------------|----------|--------------------|-------------------------|
| Cogno, runy amou |          | Steelmaking Method |                         |
| Product          | Heat     | Test Type          |                         |
| 0.21             | 0.20     | C                  |                         |
| 0.95             | 0.92     | Mn                 |                         |
| 0.015            | 0.016    | Р                  |                         |
| 0.00             | 0.001    | S                  | Chemical                |
| 1 0.31           | 0.33     | Si                 | Chemical Analysis (wt%) |
| 20.0             | 0.06     | Cr                 | wt%)                    |
| 0.09             | 0.07     | Си                 |                         |
| 0.01             | 0.01     | Mo                 |                         |
| 0.03             | 0.02     | Ni                 |                         |
| 0.003            | 0.005    | ٧                  |                         |
| 0.001            | 0.002    | Ti                 |                         |
| 0.001            | 0.001    | Nb                 |                         |
| 0.0001           | 0.0003   | В                  |                         |
| 0.39             | -        | CE(IIW)            |                         |
| 0.39             | 1        | CE(CSA)            |                         |

| В                           | Г          |                 | Т                     |
|-----------------------------|------------|-----------------|-----------------------|
| BSM-1298                    |            | Heat            |                       |
| Heat                        |            | Test Type       |                       |
| Ferrite & Pearlite          |            | Microstructure  |                       |
| 75 HRBW                     |            | Hardness        |                       |
| Pass                        |            | Flattening Test |                       |
| Longitudinal; 19.05 mm x WT | 50mm GL    | Tension Test    | Mechanical Properties |
| 45,800                      | psi        | Yield (Rt0.5)   |                       |
| 70,000                      | psi        | Tensile (Rm)    |                       |
| 0.65                        | (Rt0.5/Rm) | Т/ү             |                       |
| 47                          | %          | Elongation (A)  |                       |

| œ.       | Γ              |             |
|----------|----------------|-------------|
| BSM-1298 |                | Heat        |
| ı        | Standard       | Test        |
| 1        | Sample Details | Impact Test |
| -        | °C             | Temp        |
| 1        | J              |             |
| ı        | J              | Impact      |
| ı        | J              | Energy      |
| Ľ        | AVG            |             |
| r        | %              |             |
| ı        | %              | % Shear     |
| -        | %              | ear         |
| 1        | AVG            |             |
|          | mm             |             |
| 1        | mm             | Lateral Ex  |
| 1        | mm             | xpansion    |
| 1        | AVG            |             |

## Additional Details:

- $\checkmark$  We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with ASTM/ASME A/SA106-2011 Grade B/C A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements.
- √ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2010 Section 2.1
- ✓ No weld repairs have been performed on this product.
- ✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- $\checkmark$  This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.
- \* Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

Bouden 2013 OCT 18

Assistant QA Manager Paul Sowden, T.T.