

Product:

Seamless Carbon Steel Pipe

## Mill Test Certificate

Bri-Steel Manufacturing Inc. 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986 www.brichemsteel.com

Product Heat Number: BSM-1328 Product Size: 16 SCH 100 Production Date: Oct 15, 2013

**Product Standards:** Production Method: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010 **Hot Expansion Product Heat Treatment:** As-rolled Certificate No.: MTR- 000538

**Product Markings** 

	BS	Г	0,9,00	
	BSM-1328		Heat	
	Heat		Test Type	
	NPS 16 SCH 100 1.031in. WT		Product Size	Product: Details
	1		Pieces	
	DRL		Length	
	164.8	lb/ft	Mass	
	<5	μR/hr	Geiger	
	<10	Gauss	Res. Mag.	
	Pass	Insp.	Visual	
	Pass		9	No
	Pass	WT	UT	on-Destruc
The second second second	Pass	ASTM E213	IJ	Non-Destructive Testing
	Pass	ASTM	ET	
	*		HydroTest	
	Plain End	Condition	End	

	BSM-1328	Heat	
		eat	
Degas, rully villed	Blast Furnace; EAF; Ladle Refining; Vacuum	Steelmaking Method	
Product	Heat	Test Type	
0.21	0.20	С	
0.88	0.91	Mn	
0.014	0.013	P	
0.004	0.002	S	Chemical
0.32	0.32	Si	Chemical Analysis (wt%)
0.05	0.04	Cr	wt%)
0.07	0.06	Cu	
0.01	0.01	Mo	
0.03	0.02	N:	
0.003	0.002	٧	
0.001	0.001	Ti	
100.0	0.001	Nb	
0.0001	0.0002	В	
0.37		CE(IIW)	
0.37	1	CE(CSA)	

	_			_
	BSM-1328		Heat	
	Heat		Test Type	
	Ferrite & Pearlite		Microstructure	
	78 HRBW		Hardness	
	Pass		Flattening Test	
	Longitudinal; 19.05 mm x WT	50mm GL	Tension Test	Mechanical Properties
	51,500	psi	Yield (Rt0.5)	
	74,000	psi	Tensile (Rm)	
The second secon	0.70	(Rt0.5/Rm)	Υ/Τ	
The second secon	46	%	Elongation (A)	

BSM-1328		Heat	
r	Standard	Test	
f.	Sample Details	Impact Test	
·	°C	Temp	
	J		
_	Į	Impact	
L	_	t Energy	
t	AVG		
ı	%		
t	%	% Shear	
1	%		
	AVG		
	mm	Lateral Expansion	
1	mm		
t	mm		
т	AVG		

## Additional Details:

- $\checkmark$  We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with ASTM/ASME A/SA106-2011 Grade B/C A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements.
- √ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2010 Section 2.1
- No weld repairs have been performed on this product.
- √ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- $\checkmark$  This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

\* Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by: Gentler

Assistant QA Manager

Paul Sowden, T.T.

2013 OCT 24