

## Mill Test Certificate

Bri-Steel Manufacturing Inc. 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Oct 24, 2013

Seamless Carbon Steel Pipe Product Heat Number: BSM-1354 Product Size: 24 TRUE 80 Production Date:

Product:

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Certificate No.: MTR- 000564

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010

Product Markings

NPS 24 TRUE 80 1.219 INCHWT SMLS 2013/10 NDE MANUFARE HEAT BSM-1354 (PIPE # LENGTH MASS) 296.41b/ft ASTM/ASME A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

| Heat Test Type Product Size Pieces Length Mass Geiger Res. Mag.   Visual OD ** UT UT ET HydroTest    |
|--|
| lb/ft μR/hr Gauss Insp. WT ASTM E213 ASTM E309 Condition   |
| BSM-1354 Heat NPS 24 TRUE 80 1.219 in. WT 4 DRL 296.4 <5 <10 Pass Pass Pass Pass Pass Pass • Plain i |

|          |  |              |      |      | Ω     | Chemical Analysis (wt%) | Analysis | (wt%) |      |      |      |       |       |       |        |         |         |
|----------|--|--------------|------|------|-------|-------------------------|----------|-------|------|------|------|-------|-------|-------|--------|---------|---------|
| Heat     | Steelmaking Method   | Test Type    | C    | Mn   | d     | S                       | Si       | Cr    | Cu   | Mo   | iN   | Λ     | Ti    | Nb    | В      | CE(IIW) | CE(CSA) |
| BSM-1354 | Blast Furnace, EAF; Ladle Refining: Vacuum   | Heat         | 0.21 | 0.93 | 0.001 | 0.004 0.34              | 0.34     | 0.06  | 0.06 | 0.02 | 80.0 | 500.0 | 0.002 | 0.001 | 0.0003 |         | 1       |
|          | Control of the contro | Product 0.22 | 0.22 | 0.94 | 0.013 | 0.94 0.013 0.008        | 0.30     | 0.06  | 0.05 | 0.02 | 0.02 | 0.002 | 0.002 | 0.001 | 0.0003 | 0.40    | 0.40    |
|          |  |              |      |      |       |                         |          |       |      |      |      |       |       |       |        |         |         |

| BSM-1354                    |            | Heat            |                       |
|-----------------------------|------------|-----------------|-----------------------|
| 4 Heat                      |            | Test Type       |                       |
| Ferrite & Pearlite          |            | Microstructure  |                       |
| 76 HRBW                     |            | Hardness        |                       |
| Pass                        |            | Flattening Test | N                     |
| Longitudinal; 19.05 mm x WT | 50mm GL    | Tension Test    | Mechanical Properties |
| 44,200                      | psi        | Yield (Rt0.5)   |                       |
| 71,000                      | psi        | Tensile (Rm)    |                       |
| 0.62                        | (Rt0.5/Rm) | T/Y             |                       |
| 52                          | ×          | Elongation (A)  |                       |

| BSM-1354 | Sta            | Heat         |
|----------|----------------|--------------|
| ,        | Standard       | Test         |
| •        | Sample Details | Impact Test  |
| ,        | °C             | Temp         |
| 1        | J              |              |
| ı        | J              | Impact Energ |
| •        | J              | Energy       |
| 6        | AVG            |              |
| •        | %              |              |
|          | %              | % Shear      |
|          | %              | ear          |
|          | AVG            |              |
| •        | mm             | 1            |
| ,        | mm             | ateral Ex,   |
| *        | mm             | xpansion     |
| 1        | AVG            |              |

## Additional Details:

- $\checkmark$  We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing that the results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA105-2011 Grade B/C A/SA53-2012, and the purchase order requirements, and
- √ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3
  Sour Service-2009 NACE MR0103-2010 Section 2.1
- No weld repairs have been performed on this product.
- This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- $\prime$  This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.
- Note that this product was hydrotested to 1000 psi for 5 seconds.
- \*\*OD Tolerances as per API

Mill Test Certificate approved by:

2013 OCT 3,

Assistant QA Manager Paul Sowden, T.T.