

Mill Test Certificate

Bri-Steel Manufacturing Inc. 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986 www.bri-steel.com

Product: Seamless Carbon Steel Pipe

Production Method:

Hot Expansion

Product Heat Number:

BSM-1725

Product Size: 16S100

Production Date: Mar 25, 2014

Product Heat Treatment: As-rolled

Certificate No.: MTR- 000995

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2013 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010

Product Markings NPS 16 SCH 100 1.031 INCHWT SMLS 2014/03 NDE

HEAT BSM-1725 (PIPE # LENGTH MASS) 164.8lb/ft ASTM/ASME A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

-														
Plain En	*	Pass	Pass	Pass	Pass	Pass	<10	<5	164.8	DRL	1	NPS 16 SCH 100 1.031in. WT	Heat	BSM-1725
Conditio		ASTM	ASTM E213 ASTM	WT		Insp.	Gauss	μR/hr	lb/ft					
End	HydroTest	ET	5	T	OD	Visual	Res. Mag.	Geiger	Mass	Length	Pieces	Product Size	Test Type	Heat
			Non-Destructive Testing	on-Destruc	Ž							Product: Details		

0.39	0.39	0.0003	0.001	0.003	0.004	0.03	0.01	0.06	0.06	0.30	0.002	0.016	0.92	0.22	Product	Congress, Total & Name of	
1		0.0002	0.001	0.001	0.003	0.02	0.00	0.07	0.06	0.29	0.002	0.014	0.88	0.20	Heat	Blast Furnace; EAF; Ladle Refining; Vacuum	BSM-1725
CE(CSA)	CE(IIW)	В	Nb	Ті	٧	Ni	Mo	Си	Cr	Si	S	P	Μ'n	C	Test Type	Steelmaking Method	Heat
									(wt%)	Analysis	Chemical Analysis						

BSM-1725 Heat Ferrite & Pearlite		Heat Test Type Microstructure	
78 HRBW		Hardness	
Pass		Flattening Test	
Longitudinal; 19.05 mm x WT	50mm GL	Tension Test	Mechanical Properties
51,500	psi	Yield (Rt0.5)	
71,000	psi	Tensile (Rm)	
0.73	(Rt0.5/Rm)	۲/۲	
46	%	Elongation (A)	

L	i	Ĭ.		t	r	1		ı	ŧ		BSM-1725
AVG	%	%	%	AVG	Į	_	J	റ്	Sample Details	Standard	
	% Shear	% SI			: Energy	Impact		Temp	Impact Test	Test	Heat

Additional Details:

- 🗸 We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with ASTM/ASME A/SA106-2013 Grade B/C A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements.
- √ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2010 Section 2.1
- ✓ No weld repairs have been performed on this product.
- \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.
- * Note that this product was hydrotested to 1000 psi for 5 seconds.

Mill Test Certificate approved by:

18 Somden 2014 AFROY

Assistant QA Manager Paul Sowden, T.T.